

# ISO 4960:2007-12 (E)

## Cold-reduced carbon steel strip with a mass fraction of carbon over 0,25 %

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>2</b>
<b>4</b>	<b>Specified qualities appropriate to the particular grade .....</b>	<b>2</b>
<b>5</b>	<b>Conditions of manufacture .....</b>	<b>3</b>
<b>5.1</b>	<b>Steelmaking .....</b>	<b>3</b>
<b>5.2</b>	<b>Chemical composition .....</b>	<b>3</b>
<b>5.3</b>	<b>Heat analysis .....</b>	<b>3</b>
<b>5.4</b>	<b>Product analysis .....</b>	<b>3</b>
<b>5.5</b>	<b>Surface finish .....</b>	<b>5</b>
<b>5.6</b>	<b>Oiling .....</b>	<b>5</b>
<b>5.7</b>	<b>Weldability .....</b>	<b>5</b>
<b>5.8</b>	<b>Application .....</b>	<b>5</b>
<b>5.9</b>	<b>Mechanical properties .....</b>	<b>5</b>
<b>6</b>	<b>Ordering requirements and dimensional tolerances .....</b>	<b>8</b>
<b>6.1</b>	<b>Ordering requirements .....</b>	<b>8</b>
<b>6.2</b>	<b>Dimensional tolerances .....</b>	<b>8</b>
<b>7</b>	<b>Sampling .....</b>	<b>8</b>
<b>8</b>	<b>Mechanical property tests .....</b>	<b>8</b>
<b>8.1</b>	<b>Hardness test .....</b>	<b>8</b>
<b>8.2</b>	<b>Tensile test .....</b>	<b>8</b>
<b>9</b>	<b>Decarburization .....</b>	<b>9</b>
<b>10</b>	<b>Retests .....</b>	<b>9</b>
<b>10.1</b>	<b>Machining and flaws .....</b>	<b>9</b>
<b>10.2</b>	<b>Additional tests .....</b>	<b>9</b>
<b>11</b>	<b>Resubmission .....</b>	<b>11</b>
<b>12</b>	<b>Workmanship .....</b>	<b>11</b>
<b>13</b>	<b>Inspection and acceptance .....</b>	<b>11</b>
<b>14</b>	<b>Coil size .....</b>	<b>11</b>
<b>15</b>	<b>Marking .....</b>	<b>11</b>
<b>16</b>	<b>Information to be supplied by the purchaser .....</b>	<b>12</b>
<b>Bibliography .....</b>		<b>13</b>