ISO 23475-1:2021-02 (E)

Testing method for steel tyre cord - Part 1: General requirements

Contents

Page

Foreword ..... **v**

1 Scope **1**

2 Normative references **1**

3 Terms and definitions **1**

4 Dimension **1**

4.1 Cord diameter 1

4.1.1 Measure with micrometre 1

4.1.2 Measure with profile projector 3

4.2 Unravelled filament diameter 4

4.2.1 Principle 4

4.2.2 Apparatus 4

4.2.3 Procedure 5

4.2.4 Expression of results 5

4.2.5 Test report 5

4.3 Linear density 5

4.3.1 Principle 5

4.3.2 Apparatus 5

4.3.3 Procedure 6

4.3.4 Test report 6

4.4 Lay direction and lay length 6

4.4.1 Lay direction/direction of lay 6

4.4.2 Trace method for lay length 6

4.4.3 Untwisting method for lay length 8

5 Process property **9**

5.1 Straightness 9

5.1.1 Principle 9

5.1.2 Apparatus 9

5.1.3 Procedure 9

5.1.4 Test report 9

5.2 Arc height 9

5.2.1 Principle 9

5.2.2 Apparatus 10

5.2.3 Procedure 10

5.2.4 Test report 10

5.3 Flare 10

5.3.1 Principle 10

5.3.2 Apparatus 10

5.3.3 Procedure 10

5.3.4 Test report 11

5.4 Residual torsion 11

5.4.1 Principle 11

5.4.2 Apparatus 11

5.4.3 Procedure 11

5.4.4 Test report 11

6 Mechanical property **12**

6.1 Breaking load and elongation at fracture 12

6.1.1 Principle 12

6.1.2 Apparatus 12

6.1.3 Procedure 12

6.1.4 Test report 13

6.2 Elongation between defined forces (EDF) 13
6.2.1 Principle 13
6.2.2 Apparatus 14
6.2.3 Procedure 15
6.2.4 Test report 15
6.3 Loop test (Elasticity) 15
6.3.1 Principle 15
6.3.2 Apparatus 15
6.3.3 Procedure 16
6.3.4 Test report 17
7 Determination of mass and composition of coating by X-Ray fluorescence spectroscopy 17
7.1 Principle 17
7.2 Apparatus 17
7.2.1 WDXRFS or EDXRFS 17
7.2.2 Analytical balance, which can be read to the nearest 0,001 g. 17
7.2.3 Dispenser, with the accuracy of 25,00 ml ± 0,05 ml. 17
7.2.4 X/Y shaker, with variable frequency. 17
7.3 Reagents 17
7.3.1 Acetone or diethyl ether 17
7.3.2 Ammonium persulphate (mass fraction >98 %) 17
7.3.3 Ammonia (mass fraction >25 %, not more than "***d***=0,91" at temperature 20 °C) 17
7.3.4 Stripping solution, for 1 l: weigh 16 g ammonia persulphate into a beaker of 600 ml and dissolve in 400 ml demineralized water. Transfer quantitatively into a 1 l volumetric flask. Add 120 ml ammonia. Fill up to the mark with demineralized water. Shake well. 17
7.3.5 Standard, the matrix and range should cover the sample range. Prepare the calibration standards according to the XRFS user's manual or according to an example in Table 1. 17
7.4 Preparation of test samples 18
7.5 Procedure 18
7.6 Expression of results 18
7.7 Test report 19