

# ISO 10280:2025-09 (E)

## Steel and iron - Determination of titanium content - Diantipyrylmethane spectrophotometric method

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>1</b>
<b>4</b>	<b>Principle .....</b>	<b>1</b>
<b>5</b>	<b>Reagents .....</b>	<b>1</b>
<b>6</b>	<b>Apparatus .....</b>	<b>3</b>
<b>7</b>	<b>Sampling and preparation of the test samples .....</b>	<b>3</b>
<b>8</b>	<b>Procedure .....</b>	<b>3</b>
<b>8.1</b>	<b>Test portion .....</b>	<b>3</b>
<b>8.2</b>	<b>Blank test .....</b>	<b>3</b>
<b>8.3</b>	<b>Determination .....</b>	<b>3</b>
<b>8.3.1</b>	<b>Dissolution of the test portion .....</b>	<b>3</b>
<b>8.3.2</b>	<b>Treatment of insoluble residue .....</b>	<b>4</b>
<b>8.3.3</b>	<b>Colour development .....</b>	<b>4</b>
<b>8.3.4</b>	<b>Spectrophotometric measurements .....</b>	<b>5</b>
<b>8.4</b>	<b>Establishment of the calibration curves .....</b>	<b>5</b>
<b>8.4.1</b>	<b>Preparation of the calibration solutions .....</b>	<b>5</b>
<b>8.4.2</b>	<b>Spectrophotometric measurements .....</b>	<b>6</b>
<b>8.4.3</b>	<b>Calibration curves .....</b>	<b>6</b>
<b>9</b>	<b>Expression of results .....</b>	<b>7</b>
<b>9.1</b>	<b>Method of calculation .....</b>	<b>7</b>
<b>9.2</b>	<b>Precision .....</b>	<b>7</b>
<b>10</b>	<b>Test report .....</b>	<b>8</b>
<b>Annex A (informative) Additional information on the international precision tests .....</b>		<b>9</b>
<b>Annex B (informative) Graphical representation of precision data .....</b>		<b>11</b>
<b>Bibliography .....</b>		<b>12</b>