

# DIN EN ISO 62:2008-05 (E)

## Plastics - Determination of water absorption (ISO 62:2008)

---

<b>Contents</b>		<b>Page</b>
Foreword .....		3
Introduction .....		4
<b>1</b>	<b>Scope .....</b>	<b>5</b>
<b>2</b>	<b>Normative references .....</b>	<b>5</b>
<b>3</b>	<b>Principle .....</b>	<b>6</b>
<b>4</b>	<b>Apparatus .....</b>	<b>6</b>
<b>5</b>	<b>Test specimens .....</b>	<b>6</b>
5.1	General .....	6
5.2	Square-shaped test specimens for homogeneous plastics .....	7
5.3	Test specimens of reinforced plastics affected by anisotropic diffusion effects .....	7
5.4	Tubular test specimens .....	7
5.5	Rod-shaped test specimens .....	8
5.6	Specimens cut from finished products, extrusion compounds, sheets or laminates .....	8
<b>6</b>	<b>Test conditions and procedures .....</b>	<b>8</b>
6.1	General .....	8
6.2	General conditions .....	8
6.3	Method 1: Determination of amount of water absorbed after immersion in water at 23 °C ...	9
6.4	Method 2: Determination of amount of water absorbed after immersion in boiling water .....	9
6.5	Method 3: Determination of water-soluble matter lost during immersion .....	10
6.6	Method 4: Determination of amount of water absorbed after exposure to 50 % relative humidity .....	10
<b>7</b>	<b>Expression of results .....</b>	<b>10</b>
7.1	Percentage by mass of water absorbed .....	10
7.2	Determination of the water content at saturation and the water diffusion coefficient using Fick's laws .....	11
<b>8</b>	<b>Precision .....</b>	<b>12</b>
<b>9</b>	<b>Test report .....</b>	<b>13</b>
<b>Annex A (informative)</b>	<b>Correlation between water absorption by test specimens and Fick's diffusion laws .....</b>	<b>14</b>
<b>Annex B (informative)</b>	<b>Precision statement .....</b>	<b>16</b>
<b>Bibliography .....</b>		<b>19</b>