

DIN 8078:2008-09 (E)

Polypropylene (PP) pipes - PP-H, PP-B, PP-R, PP-RCT - General quality requirements and testing

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Material	4
3.1	General	4
3.2	Proof of long-term hydrostatic strength	5
4	Requirements	10
4.1	Delivery condition	10
4.2	Surface condition	10
4.3	Dimensions and tolerances	10
4.4	Long-term hydrostatic strength	10
4.5	Impact strength test behaviour (inspection by attributes)	10
4.6	Changes after heat treatment	10
5	Testing	11
5.1	Surface condition	11
5.2	Dimensions	11
5.3	Out-of-roundness (ovality)	11
5.4	Long-term hydrostatic strength test	12
5.5	Impact strength test (inspection by attributes)	13
5.6	Heat reversion	14
5.7	Inspection documents	14
Annex A (informative)	Explanatory notes	15
Bibliography		17
Figures	Figure 1 -- Reference characteristic curves of the long-term hydrostatic strength (minimum curves) for PP-H pipes	6
	Figure 2 -- Reference characteristic curves of the long-term hydrostatic strength (minimum curves) for PP-B pipes	7
	Figure 3 -- Reference characteristic curves of the long-term hydrostatic strength (minimum curves) for PP-R pipes	8
	Figure 4 -- Reference characteristic curves of the long-term hydrostatic strength (minimum curves) for PP-RCT pipes	9
	Figure 5 -- Test pieces for long-term hydrostatic test	12
	Figure 6 -- Bar-shaped test piece for impact strength test	13
Tables	Table 1 -- Coefficients for calculating the reference characteristic curves	5
	Table 2 -- Test conditions for the long-term hydrostatic test	11

Table 3 -- Impact strength test pieces	14
Table 4 -- Test conditions for heat treatment	14
Table A.1 -- Guideline values for some properties of PP materials	16