

DIN EN 15860:2012-01 (E)

Plastics - Thermoplastic semi-finished products for machining - Requirements and test methods

Contents		Page
Foreword		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	Materials	6
5	Requirements	8
5.1	As-delivered condition	8
5.2	Surface appearance	8
5.3	Dimensions and tolerances for rods	8
5.3.1	Diameter	8
5.3.2	Length	10
5.3.3	Roundness	10
5.3.4	Straightness	11
5.4	Dimensions and tolerances for hollow bars	12
5.4.1	Diameters	12
5.4.2	Length	14
5.4.3	Roundness	14
5.4.4	Straightness	14
5.4.5	Concentricity	15
5.5	Dimensions and tolerances for panels/plates	16
5.5.1	Thickness	16
5.5.2	Length and width	17
5.5.3	Straightness	17
5.6	Properties	20
5.6.1	Physical properties	20
5.6.2	Dimensional stability after heat treatment	24
5.6.3	Physiological behaviour	26
6	Test methods	26
6.1	Test conditions	26
6.2	Sampling size	26
6.3	Test specimen preparation	26
6.3.1	Mechanical properties	26
6.3.2	Density	28
6.3.3	Melt volume-flow rate, viscosity number, melting temperature/glass transition temperature	28
6.3.4	Dimensional stability after heat treatment	28
6.4	As-delivered condition	29
6.5	Surface appearance	29
6.6	Accuracy of the dimension measuring instruments	29
6.7	Density	29
6.8	Tensile stress at yield and elongation at break	29
6.9	Tensile modulus of elasticity	30
6.10	Vicat softening temperature	30
6.11	Melt volume-flow rate (MVR)	30
6.12	Melting temperature/glass transition temperature	31

6.13	Viscosity number	31
6.14	Dimensional stability after heat treatment	31
6.15	Preparation of test results	35
7	Designation	35
7.1	Rods	35
7.2	Hollow bars	35
7.3	Panels/plates	36
8	Marking	36
Annex A (normative) Procedure for the determination of microporosity in semi-finished products ..		37
Annex B (normative) Tables for the conversion of deflection values (straightness)		41
Annex C (informative) Examples of calculation of dimensional stability after heat treatment		44
C.1	Rods	44
C.2	Hollow bars	44
C.3	Panels/plates	45
Bibliography		46