

ISO 1133-2:2011-12 (E)

Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics - Part 2: Method for materials sensitive to time-temperature history and/or moisture

Contents		Page
	Foreword	iv
	Introduction	v
1	Scope	1
2	Normative references	2
3	Terms and definitions	2
4	Principle	2
5	Apparatus	2
5.1	Extrusion plastometer	2
5.2	Accessory equipment	3
6	Test sample	4
6.1	Sample form	4
6.2	Sample pre-treatment and storage	4
7	Temperature verification, cleaning and maintenance of the apparatus	5
7.1	Verification of the temperature-control system	5
7.2	Cleaning the apparatus	5
7.3	Vertical alignment of the instrument	5
8	Procedural set-up	5
8.1	General	5
8.2	Selection of temperature and load	6
8.3	Cleaning	6
8.4	Selection of sample mass and charging the cylinder	6
9	Procedure	7
9.1	Selection of temperature and load	7
9.2	Minimum piston displacement distance	7
9.3	Timer device	7
9.4	Preparation for the test	7
9.5	Measurement	7
9.6	Expression of results	8
10	Flow rate ratio (FRR)	8
11	Precision	8
12	Test report	9
	Annex A (informative) Verification of temperature in the cylinder	10
	Annex B (informative) Repeated MVR determinations on different materials carried out in line with this Bibliography	16