

DIN EN ISO 17556:2012-12 (E)

Plastics - Determination of the ultimate aerobic biodegradability of plastic materials in soil by measuring the oxygen demand in a respirometer or the amount of carbon dioxide evolved (ISO 17556:2012)

Contents	Page
Foreword	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Principle	7
5 Test environment	8
6 Materials	8
7 Apparatus	8
8 Procedure	8
8.1 Preparation of the test material	8
8.2 Preparation of the reference material	9
8.3 Preparation of the test soil	9
8.4 Start-up and execution of the test	11
9 Calculation and expression of results	13
9.1 Calculation	13
9.2 Expression and interpretation of results	14
10 Validity of results	14
11 Test report	14
Annex A (informative) Principle of a manometric respirometer (example)	16
Annex B (informative) Example of a system for measuring the amount of carbon dioxide evolved ...	17
Annex C (informative) Examples of methods for the determination of evolved carbon dioxide	18
Annex D (informative) Theoretical oxygen demand (ThOD)	20
Annex E (informative) Example of a determination of the amount and the molecular mass of water-insoluble polymer remaining at the end of a biodegradation test	21
Annex F (informative) Examples of long-term tests	22
Annex G (informative) Round-robin testing	26
Bibliography	30