

ISO 6721-8:2019 (E)

Plastics — Determination of dynamic mechanical properties — Part 8: Longitudinal and shear vibration — Wave-propagation method

Contents

	Foreword
1	Scope
2	Normative references
3	Terms and definitions
4	Principle
5	Testing device
5.1	Apparatus
5.1.1	Method A: Immersion method
5.1.2	Method B: Transducer contact method
5.2	Transducers
5.3	Transit-time measurement equipment
5.4	Temperature measurement and control
6	Test specimens
6.1	General
6.2	Shape and dimensions
6.3	Preparation
7	Number of specimens
8	Conditioning
9	Procedure
9.1	Test atmosphere
9.2	Measuring the specimen dimension
9.3	Performing the test
9.3.1	Method A: Immersion method
9.3.2	Method B: Transducer contact method
9.3.3	Measurement of the specimen density
9.4	Varying the temperature
10	Expression of the results
10.1	Symbols
10.2	Determination of the longitudinal wave velocity v_L
10.2.1	Method A: Immersion method
10.2.2	Method B: Transducer contact method
10.3	Determination of the transverse wave velocity v_T
10.3.1	Method A: Immersion method
10.3.2	Method B: Transducer contact method
10.4	Calculation of dynamic properties
10.5	Influence of material anisotropy
11	Precision
12	Test report

