ISO 16486-1:2020 (E)

Plastics piping systems for the supply of gaseous fuels — Unplasticized polyamide (PA-U) piping systems with fusion jointing and mechanical jointing — Part 1: General

Contents

Foreword

Introduction

1 Scope

2 Normative references

3 Terms and definitions

3.1 Geometrical characteristics
3.2 Materials
3.3 Material characteristics
3.4 Related to service conditions

4 Symbols and abbreviated terms

4.1 Symbols
4.2 Abbreviated terms

5 Material

5.1 Material of the components
5.2 Compound
5.2.1 Additives
5.2.2 Colour
5.2.3 Identification compound
5.2.4 Rework material
5.2.5 Characteristics
5.2.6 Change of compound formulation
5.3 Fusion compatibility
5.4 Classification and designation
5.5 Maximum operating pressure (MOP)
5.6 Effects of transport of liquid hydrocarbons and hydrogen

Annex A (normative) Assessment of degree of pigment or carbon black dispersion in unplasticized polyamide compounds

A.1 Apparatus
A.2 Procedure
A.3 Requirements
A.4 Test report

Annex B (normative) Chemical resistance

B.1 Principle
B.2 Reagents
B.3 Control fluids
B.4 Test pieces
B.5 Conditioning of test pieces and reagents
B.6 Procedure
B.6.1 Determination of the hoop stress at burst
B.6.2 Determination of the tensile strength at yield
B.7 Test report

Annex C (normative) Hoop stress at burst

C.1 Principle

C.2 Apparatus
C.3 Test pieces
C.3.1 Preparation of test pieces
C.3.2 Number of test pieces
C.4 Procedure
C.5 Test report

Annex D (informative) Continuous liquid hydrocarbon exposure from transported fluid or soil contamination

D.1 General

Annex E (informative) Permeation resistance against different gases

E.1 Release of methane from pressurized PA-U 11 and PA-U 12 Pipes
E.2 Release of hydrogen from pressurized PA-U 11 and PA-U 12 Pipes
E.3 Release of mixture of methane and hydrogen from pressurized PA-U 11 Pipes
E.4 Effect of long-term hydrogen exposure on PA-U as investigated at PA-U 11 Pipes

Page count: 25