

DIN EN ISO 11357-8:2021-05 (E)

Plastics - Differential scanning calorimetry (DSC) - Part 8: Determination of thermal conductivity (ISO 11357-8:2021)

Contents	Page
European foreword	3
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Principle	6
5 Apparatus and substances	7
5.1 DSC instrument	7
5.2 Crucibles	7
5.3 Melting substance	7
5.4 Protective lacquer	8
5.5 Length measuring device	8
6 Specimens	8
6.1 Geometry	8
6.2 Number and sampling	8
7 Conditioning	8
8 Calibration	9
9 Measurement procedure	9
9.1 Preparation of crucibles	9
9.2 Use of thermal contact substances	9
9.3 Measurement of melting substance	9
9.3.1 Placing of crucibles in sample holder	9
9.3.2 Distribution of melting substance on crucible ground	9
9.3.3 Measurement of the slope of the melting curve without test specimen	10
9.3.4 Insertion of test specimen	10
9.3.5 Measurement of the slope of the melting curve with test specimen	10
9.4 Evaluation of the slope of the peaks of the melting substance	10
10 Calculation of thermal conductivity	12
11 Service life of crucibles upon using gallium as melting substance	12
12 Precision and bias	12
13 Test report	13
Annex A (informative) Interlaboratory determination of thermal conductivity measured by means of DSC	14
Bibliography	17