

DIN EN ISO 527-5:2022-05 (E)

Plastics - Determination of tensile properties - Part 5: Test conditions for unidirectional fibre-reinforced plastic composites (ISO 527-5:2021)

Contents	Page
European foreword	3
Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	9
5 Apparatus	9
6 Test specimens	9
6.1 Shape and dimensions	9
6.1.1 General	9
6.1.2 Type A specimen (for longitudinal direction)	11
6.1.3 Type B specimen (for transverse direction)	11
6.2 Preparation of specimens	11
6.2.1 General	11
6.2.2 End tabs	11
6.2.3 Application of end tabs	11
6.3 Gauge marks	11
6.4 Checking the specimens	11
7 Number of specimens	12
8 Conditioning	12
9 Procedure	12
9.1 Test atmosphere	12
9.2 Measurement of specimen dimensions	12
9.3 Clamping	12
9.4 Prestresses	12
9.5 Setting of extensometers and strain gauges and placing of gauge marks	12
9.6 Test speed	12
9.7 Recording of data	12
10 Calculation and expression of results	12
10.1 Calculation of all properties for parallel sided specimens (Type A and B)	12
11 Precision	13
12 Test report	13
Annex A (informative) Alignment of specimens	14
Annex B (informative) Use of unbonded tabs and conditions for gripping tab-less specimens using fine grip faces	16
Annex C (normative) Specimen preparation for type A and type B	19
Bibliography	21