

ISO 15024:2023-02 (E)

Fibre-reinforced plastic composites - Determination of mode I interlaminar fracture toughness, GIC, for unidirectionally reinforced materials

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Apparatus	6
5.1	Test machine	6
5.1.1	General	6
5.1.2	Speed of testing	7
5.1.3	Fixture	7
5.1.4	Load and displacement measurements	7
5.1.5	Recorder	7
5.2	Load blocks or piano hinges	7
5.3	Measuring apparatus	7
5.4	Travelling microscope (optional)	7
5.5	Non-adhesive insert film	7
5.6	Ancillary equipment	8
6	Test specimen	8
6.1	Test plate preparation	8
6.2	Specimen preparation	8
6.2.1	Preferred specimens	8
6.2.2	Alternative specimens	9
6.3	Checking and measurement of the test specimens	9
6.4	Attachment of loading points	9
6.5	Measurement of delamination length	9
7	Number of specimens	9
8	Conditioning	10
9	Test procedure	10
9.1	Test set-up	10
9.2	Initial loading	10
9.3	Re-loading	11
10	Calculation of GIC	11
10.1	Interpretation of test results	11
10.2	Data reduction	12
10.2.1	General	12
10.2.2	Method A: Corrected beam theory (CBT)	12
10.2.3	Method B: Modified compliance calibration (MCC)	14
10.3	Data sheets, data plots and statistical calculation	14
11	Precision	18

12	Test report	19
	Annex A (normative) Preparation and bonding of the load blocks or piano hinges	21
	Annex B (informative) Recommendations for testing	22
	Annex C (informative) Recommended test result sheet	25
	Annex D (informative) DCB test with flat insert hinge	28
	Bibliography	32