DIN EN 515:2017-05 (E)

Aluminium and aluminium alloys - Wrought products - Temper designations

Contents

Page

European foreword 3

1 Scope 4

2 Normative references 4

3 Terms and definitions 4

4 Basis of codification 6

5 Basic temper designations 6
5.1 F - as fabricated 6
5.2 O - Annealed 6
5.3 H - Strain-hardened 6
5.4 W - Solution heat-treated 7
5.5 T - Thermally treated to produce stable tempers other than F, O or H (for heat-treatable alloys only) 7

6 Subdivision of O (annealed) temper designations 7
6.1 O1 - High temperature annealed and slow cooled 7
6.2 O2 - Thermo-mechanically processed 7
6.3 O3 - Homogenized 7

7 Subdivision of H (strain-hardened) temper designations 7

8 Subdivision of T (thermally treated to produce stable tempers other than F, O or H) temper designations 10
8.1 First digit after T 10
8.2 Additional digits added to designations T1 to T10 12
8.3 Assigned additional digits for stress-relieved T tempers 12
8.3.1 Stress-relieved by stretching 12
8.3.2 Stress-relieved by compressing 13
8.3.3 Stress-relieved by combined stretching and compressing 13
8.3.4 Assigned additional digits for stress-relieved W tempers 13
8.4 Assigned additional digits for variations of T7 type tempers 13
8.5 Demonstration of response to heat treatment 14
8.5.1 Temper designations for producer/supplier -- Laboratory demonstration of response to heat treatment 14
8.5.2 Temper designations for producer/supplier -- Demonstration of response to temper conversion 14
8.5.3 Temper designations for purchaser/user heat treatment 14

9 Summary 14

Annex A (informative) Recommendations for further T tempers extensions 23

A.1 Numeral 1 as a second digit after T 23
A.2 Numerals 1 and 3 to 9 as a second digit after T3, T8 or T9 23
A.3 Numerals 1 and 3 to 5 as a second digit after T5 or T6 23
A.4 Numeral 6 as a second digit after T5 or T6 23
A.5 Summary of possible uses of a second digit after T 23

Bibliography 25