

ISO 2107:2023-09 (E)

Aluminium and aluminium alloys - Wrought products - Temper designations

Contents		Page
	Foreword.....	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Basic temper designations	2
	4.1 F — as fabricated.....	2
	4.2 O — annealed.....	3
	4.3 H — strain-hardened.....	3
	4.4 W — solution heat-treated.....	3
	4.5 T — precipitation hardened to produce stable tempers other than F, O or H.....	3
5	Subdivisions of O temper designations	3
	5.1 O1 — high-temperature annealed to accentuate ultrasonic response and provide dimensional stability.....	3
	5.2 O3 — homogenized.....	3
6	Subdivisions of H temper designations	4
	6.1 General.....	4
	6.2 First digit after H.....	4
	6.3 Second digit after H.....	4
	6.4 Third digit after H.....	5
	6.5 Other digits after H.....	6
7	Subdivisions of T temper designations	6
	7.1 First digits (numerals 1 to 10) after T.....	6
	7.2 Additional digits added to designations T1 to T10.....	8
	7.3 Assigned additional digits for stress-relieved T tempers.....	8
	7.3.1 Stress-relieved by stretching.....	8
	7.3.2 Stress relieved by compressing.....	9
	7.3.3 Stress relieved by combined stretching and compressing.....	9
	7.4 Assigned additional digits for stress-relieved W tempers.....	9
	7.5 Assigned additional digits for variations of T7 type tempers.....	9
	7.6 Assigned additional digits for producer/supplier demonstration tempers and purchaser/user processed tempers.....	10
	7.6.1 Temper designations for producer/supplier — Laboratory demonstration of response to heat treatment.....	10
	7.6.2 Temper designations for producer/supplier — Demonstration of response to temper conversion.....	10
	7.6.3 Temper designations for purchaser/user heat treatment.....	11
	Annex A (informative) Common, regionally applied temper designations and descriptions	12