

ISO 2107:2007-02 (E)

Aluminium and aluminium alloys - Wrought products - Temper designations

Contents		Page
Foreword		iv
1	Scope	1
2	Terms and definitions	1
3	Basis of codification	2
4	Basic temper designations	2
4.1	F -- as fabricated	2
4.2	O -- annealed	2
4.3	H -- strain-hardened	2
4.4	W -- solution heat-treated	2
4.5	T -- thermally treated to produce stable tempers other than F, O or H	3
5	Subdivisions of O temper designations	3
5.1	O1 -- high-temperature annealed and slow cooled	3
5.2	O2 -- thermo-mechanically processed	3
5.3	O3 -- homogenized	3
6	Subdivisions of H temper designations	3
6.1	General	3
6.2	First digit after H	3
6.3	Second digit after H	4
6.4	Third digit after H	5
6.5	Other digits after H	5
7	Subdivisions of T temper designations	5
7.1	First digits (numerals 1 to 10) after T	5
7.2	Additional digits added to designations T1 to T10	7
7.3	Assigned additional digits for stress-relieved T tempers	7
7.4	Assigned additional digits for stress-relieved W tempers	8
7.5	Assigned additional digits for variations of T7 type tempers	8
Annex A (informative)	Demonstration of response to heat treatment	9