

DIN EN 16729-3:2018-07 (E)

Railway applications - Infrastructure - Non-destructive testing on rails in track - Part 3: Requirements for identifying internal and surface rail defects

Contents		Page
European foreword		4
Introduction		5
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Symbols and abbreviations	9
5	NDT Methods to detect internal and surface rail defects	9
5.1	General	9
5.2	Convention	9
5.3	Visual testing - VT	9
5.3.1	Description	9
5.3.2	Test area	10
5.3.3	Example applications	10
5.4	Automatic visual testing - AVT	10
5.4.1	Description	10
5.4.2	Test area	11
5.4.3	Example applications	11
5.5	Ultrasonic testing - UT	12
5.5.1	Description	12
5.5.2	Test area	12
5.5.3	Example applications	13
5.6	Eddy current testing - ET	13
5.6.1	Description	13
5.6.2	Test area	13
5.6.3	Example applications	14
5.7	Magnetic particle testing - MT	14
5.7.1	Description	14
5.7.2	Test area	15
5.7.3	Example applications	15
5.8	Penetrant testing - PT	15
5.8.1	Description	15
5.8.2	Test area	15
5.8.3	Example applications	15
5.9	Guided Wave Testing - GWT	15
5.9.1	Description	15
5.9.2	Test area	16
5.9.3	Example applications	16
6	NDT detection of internal and surface rail defects	17
6.1	General	17
6.2	Squat	20
6.3	Progressive transverse cracking	22
6.4	Horizontal cracking	24
6.5	Longitudinal vertical cracking (in the head of the rail)	26
6.6	Rail head surface conditions	29

6.7	Head check on the gauge corner	30
6.8	Corrosion	33
Annex ZA (informative) Relationship between this European Standard and the essential requirements of EU Directive 2008/57/EC aimed to be covered		35
Bibliography		37