

ISO 9466:2025-01 (E)

Railway applications - Coating of passenger rail vehicles

Contents

Page

Foreword.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms, definitions, abbreviated terms and symbols.....	3
3.1 Terms and definitions.....	3
3.2 Abbreviated terms and symbols.....	4
3.2.1 Abbreviated terms.....	4
3.2.2 Symbols.....	4
4 Coating systems, locations and environment and design recommendations.....	5
4.1 General.....	5
4.2 Types of locations.....	5
4.3 Standard support and substrates.....	5
4.4 Coating system qualification.....	6
4.4.1 General.....	6
4.4.2 Chemical and physiochemical characteristics of products for each layer.....	6
4.4.3 Application properties of products.....	8
4.4.4 Physical characteristics of products.....	10
4.4.5 Decorative characteristics.....	13
4.4.6 Mechanical characteristics.....	15
4.4.7 Ageing characteristics.....	18
4.5 Design recommendations.....	24
4.5.1 General.....	24
4.5.2 Coated parts specifications.....	24
5 Process establishment and qualification.....	24
5.1 General.....	24
5.2 Establishing the process steps.....	25
5.2.1 General.....	25
5.2.2 Ambient conditions.....	25
5.2.3 Cleaning and degreasing the surface.....	25
5.2.4 Pretreatment and surface preparation methods.....	25
5.2.5 Coating application.....	27
5.2.6 Drying.....	27
5.2.7 Inter-operation time.....	28
5.3 Process qualification.....	28
5.3.1 General.....	28
5.3.2 Tests for process qualification.....	28
5.3.3 Process qualification report.....	29
5.4 Supplier process information.....	30
6 Serial production.....	30
6.1 General.....	30
6.2 First article inspection.....	30
6.3 Local work instruction document.....	30
6.4 In-house testing of serial parts.....	32
6.4.1 General.....	32
6.4.2 Technical tests (valid for all location).....	33
6.4.3 Decorative locations.....	34

6.4.4 Traceability requirements37

6.5 Repair and maintenance37

6.5.1 Repair37

6.5.2 Maintenance37

Annex A (informative) Proposed graffiti products and graffiti remover38

**Annex B (informative) Duration level related to the refurbishment time for corrosion, humidity
and weathering tests39**

Bibliography40