

DIN EN 12680-2:2026-03 (E)

Founding - Ultrasonic testing - Part 2: Steel castings for highly stressed components

Contents		Page
European foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	5
4	Requirements	6
4.1	Order information	6
4.2	Extent of testing	6
4.3	Wall section zones	6
4.4	Maximum acceptable size of discontinuities	6
4.4.1	General	6
4.4.2	Indications without measurable dimensions	6
4.4.3	Indications with measurable dimensions	6
4.5	Qualification of personnel	7
4.6	Severity levels	8
5	Testing	8
5.1	Principles	8
5.2	Material	8
5.3	Equipment and coupling medium	9
5.3.1	Ultrasonic instrument	9
5.3.2	Probes	9
5.3.3	Checking of the ultrasonic test equipment	9
5.3.4	Coupling medium	9
5.3.5	Test sensitivity and resolution of detection	9
5.4	Preparation of casting surfaces for testing	10
5.5	Test procedure	10
5.5.1	General	10
5.5.2	Range setting	10
5.5.3	Sensitivity setting	11
5.5.4	Consideration of various types of indications	11
5.5.5	Recording limits	12
5.5.6	Evaluation of discontinuities to be recorded	12
5.5.7	Characterization and sizing of discontinuities	12
5.6	Test report	13
Annex A (normative) Resolution of detection of the instrument-probe combination		21
Annex B (informative) Sound-beam diameters		22
Annex C (informative) Types of indications generated by typical discontinuities		24
Annex D (informative) Significant technical changes between this document and the previous edition		36
Bibliography		37