

ISO 2813:2014-10 (E)

Paints and varnishes - Determination of gloss value at 20 degrees, 60 degrees and 85 degrees

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Basic principles of the gloss measurement	2
6	Apparatus and calibration equipment	4
6.1	Glossmeter	4
6.2	Measurement standards (certified reference material, working measurement standards)7	
7	Test panels	8
7.1	Substrate	8
7.2	Preparation and coating	8
7.3	Drying and conditioning	8
7.4	Thickness of coating	8
8	Calibration and adjustment of the glossmeter	8
8.1	Preparation of the apparatus	8
8.2	Zero point check	8
8.3	Calibration and adjustment	9
9	Procedure	9
9.1	Selection of geometry	9
9.2	Gloss measurement	9
10	Precision	10
10.1	General	10
10.2	Repeatability limit	10
10.3	Reproducibility limit	10
11	Test report	10
Annex A (normative) Possible sources of error		12
Annex B (normative) Calibration standards		15
Annex C (informative) Gloss calculation of primary reference standards		17
Annex D (informative) Details on precision		21
Bibliography		23