

ISO 6504-3:2019-11 (E)

Paints and varnishes - Determination of hiding power - Part 3: Determination of hiding power of paints for masonry, concrete and interior use

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols and abbreviated terms	2
5	Principle	4
6	Apparatus	4
7	Sampling	6
8	Procedure and calculation	7
8.1	Preparation of substrate	7
8.1.1	Method A (foil)	7
8.1.2	Method B and Method C (black and white charts)	7
8.2	Preparation of coated foils or black and white charts	7
8.3	Determination of the spreading rate of the test specimen	7
8.3.1	Calculation of the surface mass density	7
8.3.2	Determination of the density	9
8.3.3	Determination of the non-volatile matter	9
8.3.4	Calculation of the theoretical dry- or wet-film thickness (method A, method B and method C)	9
8.3.5	Calculation 1 - Determination of the theoretical spreading rate by calculation from the non-volatile matter content determined in accordance with ISO 3251 and the density of the coating material (see ISO 3233-3) (method A and method B)	10
8.3.6	Calculation 2 - Determination of the theoretical spreading rate calculated with the different coated masses on the two charts (method C), the density of the coating material according to ISO 2811 (all parts) and the coated area	12
8.4	Measurement of tristimulus value Y10 and calculation of the hiding power H10	13
8.4.1	General	13
8.4.2	Method A (foil)	13
8.4.3	Method B (black and white charts)	13
8.4.4	Method C (black and white charts)	13
8.5	Graphical method for determination of the hiding power at a given spreading rate (method C)	14
8.5.1	General	14
8.5.2	Determination by graphical method	14
8.5.3	Determination by calculation with a known slope	16
9	Designation of the test result	17
10	Precision	18
11	Test report	18

Annex A (informative) Details on interlaboratory comparison	20
Bibliography	22