

DIN 55633-1:2021-03 (E)

Paints and varnishes - Corrosion protection of steel structures by powder coating systems - Part 1: Assessment of powder coating systems and execution of coating

Contents	Page
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions.....	8
4 Corrosivity categories.....	10
5 Corrosion protection systems	12
5.1 General	12
5.2 Powder coating materials.....	13
5.2.1 Piece work powder coating.....	13
5.3 Durability.....	13
5.4 Requirements.....	14
5.4.1 Powder coating materials.....	14
5.4.2 Surface preparation and surface pre-treatment.....	14
5.4.3 Execution of powder coating	16
5.4.4 Film thickness of powder coating systems for piece work powder coatings.....	16
6 Corrosion protection design of the components.....	16
7 Packaging, transport, storage and assembly of components.....	17
8 Subsequent processing of powder-coated components	17
9 Testing for quality assurance	17
9.1 General	17
9.2 Test pieces.....	17
9.3 Corrosion tests	18
9.3.1 General	18
9.3.2 Coating thickness	18
9.3.3 Condensation test.....	18
9.3.4 Salt spray test	19
9.3.5 Cross-cut test	19
10 Marking of the corrosion protection system.....	19
Annex A (informative) Examples of corrosion protection systems with assignment to corrosivity categories	25
Bibliography.....	28
Figures	
Figure 1 — Salt spray test specimen.....	19

Tables

Table 1 — Categories of corrosivity of the atmosphere and examples of typical environmental conditions.....	11
Table 2 — Typical binding agents for powder coatings	13
Table 3 — Test times for atmospheric corrosivity categories	18
Table 4 — Testing the powder coating system, applied to unalloyed or low-alloy steel.....	20
Table 5 — Testing the powder coating system, applied to hot-dip galvanized steel	22
Table 6 — Assessment of the artificial ageing for the specified duration	24
Table A.1 — Examples of powder coating systems (piece work powder coating) on unalloyed steel or low alloy steel.....	26
Table A.2 — Examples of powder coating systems (piece work powder coating) on hot-dip galvanized steel.....	27