

DIN EN ISO 19403-2:2024-11 (E)

Paints and varnishes - Wettability - Part 2: Determination of the surface free energy of solid surfaces by measuring the contact angle (ISO 19403-2:2024)

Contents		Page
European foreword	3
Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus and materials	6
6 Sampling	7
7 Procedure	7
7.1 General for measuring on the horizontal drop	7
7.1.1 Setting up the contact angle measuring system	7
7.1.2 Test conditions	8
7.1.3 Conditioning of the test panels	8
7.2 Measurement	8
7.2.1 General	8
7.2.2 Static method	8
7.2.3 Dynamic method (progressive contact angle)	9
7.2.4 Determination of the contact angle	10
8 Evaluation	10
8.1 General	10
8.2 Owens-Wendt-Rabel-Kaelble method (OWRK method)	10
8.3 Wu method	11
9 Precision	12
9.1 General	12
9.2 Repeatability limit, <i>r</i>	12
9.3 Reproducibility limit, <i>R</i>	12
9.4 Calculation in accordance with the Owens-Wendt-Rabel-Kaelble method	12
10 Test report	13
Annex A (informative) Notes on measuring practice	14
Bibliography	18