

DIN EN 13381-6:2012-09 (E)

Test methods for determining the contribution to the fire resistance of structural members - Part 6: Applied protection to concrete filled hollow steel columns

Contents		Page
Foreword		4
1	Scope	6
2	Normative references	8
3	Terms and definitions, symbols and units	8
4	Test equipment	10
4.1	General	10
4.2	Furnace	10
5	Test conditions	10
5.1	General	10
5.2	Support conditions	11
5.3	Number of test specimens	11
5.4	Size of test specimens	11
5.5	Construction of steel test specimens	11
5.5.1	Short and tall concrete filled hollow columns	11
5.5.2	Application of the fire protection material	11
5.6	Composition of test specimen component materials	11
5.6.1	Steel specification	11
5.6.2	Concrete grade	12
5.6.3	Dry sand	12
5.7	Properties of test specimen component materials	12
5.7.1	Fire protection materials - General	12
5.7.2	Fire protection materials - Thickness of applied reactive protection material	12
5.8	Selection of test specimens - Principle of selection	12
6	Installation of the test specimens	13
6.1	Test specimen installation patterns	13
6.2	Furnace Load	13
6.3	Specimen mounting	13
7	Conditioning of the test specimens	13
8	Application of instrumentation	14
8.1	General	14
8.2	Instrumentation for measurement and control of furnace temperature	14
8.2.1	General	14
8.2.2	Furnace temperature in the region of test specimens	14
8.2.3	Instrumentation for the measurement of steel temperatures	14
8.3	Instrumentation for the measurement of pressure	14
9	Test procedure	14
9.1	General	14
9.2	Furnace temperature and pressure	14
9.3	Temperature of steelwork	15
9.4	Observations	15
9.5	Termination of test	15

10	Test results	15
10.1	Acceptability of test results	15
10.2	Presentation of test results in the test report	15
11	Assessment	16
11.1	General	16
11.2	Assessment procedure for thermal performance	16
12	Report of the assessment	16
13	Limits of the applicability of the results of the assessment	17
13.1	General	17
13.2	Permitted fire protection thickness range	17
13.3	Permitted minimum wall thickness	17
13.4	Permitted maximum wall thickness	17
13.5	Permitted minimum diameter	17
13.6	Permitted maximum diameter	17
	Annex A (normative) Linear interpolation analysis	21
	Annex B (normative) Application, assumptions and limitations of this European Standard	23
B.1	Structural contribution from the concrete core	23
B.2	Stickability correction	23
B.3	Thermal analysis of circular and rectangular concrete filled hollow sections	23
	Bibliography	24