

DIN EN 15497:2014-07 (E)

Structural finger jointed solid timber - Performance requirements and minimum production requirements

Contents		Page
Foreword		4
Introduction		5
1	Scope	6
2	Normative references	6
3	Terms and definitions	7
4	Symbols	9
4.1	Main symbols	9
4.2	Subscripts	9
5	Performance characteristics for structural finger jointed timber	10
5.1	Mechanical resistance	10
5.1.1	General	10
5.1.2	Timber	10
5.1.3	Bending strength of finger joints	10
5.1.4	Related material properties	10
5.2	Bonding strength and durability of bonding strength	10
5.2.1	General	10
5.2.2	Species	11
5.2.3	Adhesives for the production of structural finger jointed timber	11
5.3	Durability against biological attack	13
5.3.1	Structural finger jointed timber without preservative treatment	13
5.3.2	Structural finger jointed timber with preservative treatment	13
5.4	Resistance to fire	13
5.5	Reaction to fire	13
5.6	Formaldehyde emission	15
5.7	Release/content of other dangerous substances	15
5.8	Deviation in sizes	15
6	Assessment and Verification of Constancy of Performance (AVCP)	16
6.1	General	16
6.2	Type testing	16
6.2.1	General	16
6.2.2	Test samples, testing and compliance criteria	17
6.2.3	Test reports	19
6.2.4	Shared other party results	19
6.2.5	Cascading determination of the product type results	20
6.3	Factory production control (FPC)	21
6.3.1	General	21
6.3.2	Provisions	21
6.3.3	Product specific provisions	26
6.3.4	Initial inspection of factory and of FPC	26
6.3.5	Continuous surveillance of FPC	27
6.3.6	Procedure for modifications	27
7	Marking and labelling	27

Annex A (normative) Release of Formaldehyde	29
A.1 General	29
A.2 Classification	29
A.2.1 Provisions	29
A.2.2 Test procedure	29
A.2.3 Test report	30
Annex B (normative) Additional test methods and provisions for adhesives	31
B.1 General	31
B.2 Long-term sustained load test at cyclic climate conditions with specimens loaded perpendicular to the glue line for moisture curing one-component polyurethane and emulsion polymer isocyanate adhesives	31
B.2.1 General description	31
B.2.2 Production of the specimens	31
B.2.3 Test procedure and climate conditions	32
B.2.4 Provisions	33
B.2.5 Report	33
Annex C (normative) Bending tests with finger joints (including compliance criteria)	34
C.1 Sampling	34
C.1.1 General	34
C.1.2 For type testing	34
C.1.3 For factory production control	34
C.2 Testing	34
C.2.1 General	34
C.2.2 Additional provisions for type testing	34
C.2.3 Additional provisions for factory production control	34
C.3 Compliance criteria	35
C.3.1 For type testing	35
C.3.2 For factory production control	35
C.4 Report	35
Annex D (normative) Measurement of moisture content	37
D.1 General	37
D.2 Measurement of moisture content of timber during production	37
D.3 Mean moisture content of structural finger jointed timber	37
Annex E (normative) Equipment	38
Annex F (normative) Separation tests with finger joints produced with contact-free application of adhesive	39
Annex G (normative) Minimum production provisions	40
G.1 Personnel	40
G.2 Production and storage facilities	40
G.2.1 General	40
G.2.2 Facilities for drying and storage of timber	40
G.2.3 Facilities for processing and storage of adhesives	40
G.2.4 Facilities for production and curing	40
G.3 Equipment	40
G.4 Finger joints	41
G.4.1 Wane and edge damages	41
G.4.2 Finger joint geometry	42
G.4.3 Knots, local grain deviations and fissures	42
G.4.4 Moisture content at bonding	43
G.4.5 Bonding surface and application of the adhesive	43
G.4.6 Time between cutting and adhesive application	44

G.4.7	Pressure	44
G.4.8	Curing	45
Annex ZA (informative) Clauses of this European Standard addressing the provisions of EU Construction Products Regulation		46
Bibliography		57