

DIN EN 13381-7:2019-09 (E)

Test methods for determining the contribution to the fire resistance of structural members - Part 7: Applied protection to timber members

Contents	Page
European foreword	6
1 Scope	8
2 Normative references	9
3 Terms, definitions, symbols and units	10
3.1 Terms and definitions	10
3.2 Symbols and units	12
4 Test equipment	14
4.1 General	14
4.2 Furnace	14
4.3 Loading equipment	14
5 Test conditions	14
5.1 Test procedure	14
5.2 Support and restraint conditions	14
5.3 Loading conditions	15
6 Test specimens	16
6.1 General	16
6.2 Number	16
6.2.1 General	16
6.2.2 Fire protection system variations	17
6.3 Dimension of test specimens	17
6.4 Construction	17
6.4.1 General	17
6.4.2 Charring specimens	17
6.4.3 Large scale wall test specimen	20
6.4.4 Large scale floor test specimen	20
6.4.5 Large scale beam test specimen	20
6.4.6 Model scale test specimen	21
6.4.7 Application of the fire protection materials to the test specimen	21
6.4.8 Insulating materials	22
6.5 Composition of the test specimen components	22
6.5.1 Timber	22
6.5.2 Fire protection system	22
6.6 Properties of test materials	22
6.7 Verification of the test specimen	23
7 Installation of the test specimen	23
7.1 Large scale wall test	23
7.2 Large scale floor test	23
7.3 Large scale beam test	23
7.4 Model scale test	24
7.5 Installation patterns	24
8 Conditioning of the test specimens	24
9 Application of instrumentation	25

9.1	General	25
9.2	Instrumentation for measurement of furnace temperature	25
9.2.1	General	25
9.2.2	Large scale wall test	25
9.2.3	Large scale floor test	25
9.2.4	Large scale beam test	25
9.2.5	Model scale test	25
9.3	Instrumentation for measurement of test specimen temperature	25
9.3.1	General	25
9.3.2	Charring specimen	26
9.3.3	Large scale wall test specimen	26
9.3.4	Large scale floor test specimen	27
9.3.5	Large scale beam test specimen	27
9.3.6	Model scale test specimen	28
9.4	Instrumentation for measurement of pressure	28
9.5	Instrumentation for measurement of deformation	28
9.6	Instrumentation for measurement of applied load	28
10	Test procedure	29
10.1	General	29
10.2	Furnace temperature and pressure	29
10.3	Application and control of load	29
10.4	Temperature of test specimen	29
10.5	Deformation	29
10.6	Observations	29
10.7	Termination test	29
11	Test results	29
11.1	Acceptability of test results	29
11.1.1	General	29
11.1.2	Charring specimen	30
11.1.3	Loaded members in Large scale tests	30
11.2	Presentation of test results	30
12	Test report	31
13	Assessment	32
13.1	General	32
13.2	Assessment of the start of charring	32
13.2.1	General	32
13.2.2	Large scale test specimen	32
13.2.3	Charring specimens	33
13.3	Assessment of the charring rate	33
13.4	Assessment of failure time	34
13.4.1	General	34
13.4.2	Large scale wall test and large scale floor test	34
13.4.3	Large scale beam test	34
14	Report of the assessment	34
15	Limits of applicability of the results of the assessment	35
15.1	General	35
15.2	Limits of applicability of the assessment results	35
15.2.1	General	35
15.2.2	Thickness of fire protection material	35
15.2.3	Multiple layers	36
15.2.4	Board or panel size	36
15.2.5	Orientation of test	36
15.2.6	Timber	36
15.2.7	Insulation materials	36
15.2.8	Fixtures and fittings	37

15.3	Additional limits of applicability of the assessment results for specific construction types	37
15.3.1	Walls and floors - type of construction	37
15.3.2	Beams and columns - type of construction	37
Annex A (normative) Model scale test		58
A.1	General	58
A.2	Test equipment, installation of the specimen and test load	58
A.3	End of the model scale test	58
B.1	General	61
B.2	Fire protection systems for intended use applied timber frame walls, timber beams and timber columns:	61
B.3	Fire protection systems for intended use applied on timber frame floors, timber frame walls, timber beams and timber columns:	61
B.4	Fire protection systems for intended use applied on timber beams and timber columns:	62
Annex C (normative) Measurement of properties of fire protection materials		65
C.1	Introduction	65
C.2	Thickness of fire protection materials	65
C.2.1	General	65
C.2.2	Board or slab/mat fire protection materials	65
C.2.3	Coatings with reactive and non-reactive fire protection materials and systems	65
C.2.3.1	General	65
C.2.3.2	Measuring positions for Fire Protection Materials	66
C.3	Density of applied fire protection materials	67
C.4	Moisture content of applied fire protection materials	67
Annex D (normative) Fixing of thermocouples to timber members and timber frame assemblies and routing of cables		69
D.1	General	69
D.2	Types of thermocouples	69
D.3	Fixing of thermocouples	69
D.3.1	General	69
D.3.2	Internal thermocouples	69
D.3.3	Thermocouples at the surface of the timber member	70
D.3.4	Thermocouples in the interlayer of the fire protection system and the cavity insulation	70
D.4	Routing of thermocouple wires	70
D.4.1	General	70
D.4.2	Internal thermocouples	70
D.5	Connection of thermocouples	71
D.6	Thermocouple failures	71
Annex E (informative) Calculation of load to be applied on the large scale test specimen		74
E.1	General	74
E.2	Example 1: Load calculation for a large scale wall test specimen	74
E.3	Example 2: Load calculation for the large scale beam test	76
Annex F (informative) Examples of Assessment of Fire Protection System Performance		77
F.1	General	77
F.2	Assessment of the start of charring behind the fire protection system	77
F.3	Assessment of the charring rate behind the fire protection system	80
F.4	The time of loss of stickability of the fire protect system	81
Annex G (normative) Test method to the smouldering fire or slow heating curve		84
G.1	Introduction	84

G.2	Test equipment	84
G.3	Test conditions	84
G.4	Test specimens	84
G.5	Installation of the test specimens	84
G.6	Conditioning of the test specimens	84
G.7	Application of instrumentation	84
G.8	Test procedure	85
G.9	Test results	85
G.10	Evaluation of the results	85
Annex H (informative) Calculation of the dimensions of the charring specimen dimensions and the model scale specimen		87
H.1	Introduction	87
H.2	Calculation of the thickness of the charring specimen	87
H.3	Calculation of the number of thermocouples	88
H.4	Calculation of the charring specimen length	88
H.5	Calculation of the charring specimen width	88
H.6	Calculation of the dimensions of the model scale test specimen	88
Bibliography		90