DIN EN ISO 1716:2018-10 (E)

Reaction to fire tests for products - Determination of the gross heat of combustion (calorific value) (ISO 1716:2018)

Contents

Page

European foreword ... **3**

Foreword ... **4**

1 Scope ... **5**

2 Normative references ... **5**

3 Terms and definitions ... **5**

4 Principle ... **7**

5 Test apparatus ... **7**

6 Reagents and materials ... **12**

7 Test specimens ... **12**
7.1 General ... 12
7.2 Sampling ... 13
7.2.1 General ... 13
7.2.2 Loose-fill material ... 13
7.2.3 Liquid-applied products ... 13
7.2.4 Thin film products ... 13
7.3 Determination of surface density ... 13
7.4 Grinding ... 14
7.5 Type of specimen ... 14
7.6 Conditioning ... 14
7.7 Number of test specimens ... 14
7.8 Determination of mass ... 14
7.9 Crucible method ... 15
7.10 “Cigarette” method ... 15

8 Test procedure ... **16**
8.1 General ... 16
8.2 Calibration procedure ... 16
8.2.1 Determination of the water equivalent ... 16
8.2.2 Conditions for recalibration ... 16
8.3 Standard test procedure ... 16

9 Expression of results ... **18**
9.1 Corrections for manual apparatus ... 18
9.2 Corrections for isothermal calorimeter (see Annex C) ... 18
9.3 Calculation of the gross heat of combustion of the specimen ... 19
9.4 Calculation of the gross heat of combustion of the product ... 20
9.4.1 General ... 20
9.4.2 Homogeneous product ... 21
9.4.3 Non-homogeneous product ... 21

10 Test report ... **22**

11 Validity of test results ... **22**

Annex A (normative) **Calculation of net heat of combustion** **24**

Annex B (informative) **Precision of test method** **25**

Annex C (informative) **Calculation by graph of the corrective term, *c*, necessarybecause of the cooling of the calorimeter** **29**

Annex D (informative) **Example of determination of the gross heat ofcombustion of a non-homogeneous product** **29**

Bibliography **34**