

DIN EN 12697-5:2019-03 (E)

Bituminous mixtures - Test methods - Part 5: Determination of the maximum density

Contents		Page
European foreword		3
Introduction		5
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Principle	7
5	Materials	7
6	Apparatus	7
7	Sampling	8
8	Preparation of Sample	9
8.1	Bulk samples	9
8.2	Samples from finished material	9
8.3	Sample separation	9
9	Procedure	9
9.1	General	9
9.2	Procedure A: Volumetric procedure	9
9.3	Procedure B: Hydrostatic procedure	10
9.4	Procedure C: Mathematical procedure	11
10	Calculation	11
10.1	General	11
10.2	Procedure A: Volumetric procedure	11
10.3	Procedure B: Hydrostatic procedure	12
10.4	Procedure C: Mathematical procedure	12
11	Precision	13
11.1	General	13
11.2	Repeatability (same observer, same apparatus)	13
11.3	Reproducibility (different observers, different apparatus)	14
12	Test report	14
Annex A (informative)	General guidance on selection of a test procedure to determine the maximum density of bituminous mixtures	15
A.1	General	15
A.2	Using water and solvent	15
A.3	Using the mathematical procedure	16
Annex B (informative)	Determination of the binder absorption characteristics of the mineral aggregate for bituminous mixtures	17

Annex C (normative) Procedure for the calibration of a pycnometer	20
Bibliography	21