

DIN EN 772-5:2018-12 (E)

Methods of test for masonry units - Part 5: Determination of the active soluble salts content of clay masonry units (includes Corrigendum :2017)

Contents		Page
European foreword		3
1	Scope	4
2	Normative references	4
3	Principle	4
4	Symbols	4
5	Materials	4
5.1	For all methods	4
5.2	Instrumental method Atomic Absorption Spectroscopy (AAS) and flame photometry	5
5.3	Instrumental method Atomic Absorption Spectroscopy (AAS) and flame photometry or inductively coupled plasma spectrometry (ICP)	5
5.4	EDTA method (alternative)	5
6	Apparatus	5
7	Preparation of sample	6
7.1	Sampling	6
7.2	Crushing	6
8	Extraction procedure	6
9	Determinations of cations by instrumental techniques	6
9.1	General	6
9.2	Atomic absorption spectroscopy method (AAS) and flame photometry	6
9.2.1	Sample preparation	6
9.2.2	Calibration: preparation of the reference series	7
9.2.3	Spectroscopic lines and parameters for AAS and flame photometry analysis	7
9.3	Inductively coupled plasma spectrometry method (ICP)	8
9.3.1	General	8
9.3.2	Spectroscopic lines for ICP analysis	8
9.4	Calculation of the results	8
10	Alternative method of determination of the content of active soluble salts	9
10.1	Preparations of reagents for magnesium determination	9
10.1.1	Magnesium test solution (1,0 mg Mg/ml)	9
10.1.2	Preparation of EDTA test solution (0,5 %)	9
10.2	First titration (calcium plus magnesium)	9
10.3	Second titration (calcium)	9
10.4	Magnesium content	9
10.5	Determination of sodium and potassium	9
11	Expression of results	10
12	Test report	10