

ISO 13006:2018 (E)

Ceramic tiles — Definitions, classification, characteristics and marking

Contents

| | |
|---------|--|
| | Foreword |
| 1 | Scope |
| 2 | Normative references |
| 3 | Terms and definitions |
| 4 | Classification |
| 4.1 | Basis of classification |
| 4.2 | Methods of manufacture |
| 4.3 | Water absorption according to group |
| 4.3.1 | General |
| 4.3.2 | Subdivision of the three groups |
| 5 | Characteristics |
| 6 | Sampling and basis for acceptance |
| 7 | Requirements |
| 8 | Marking and specifications |
| 8.1 | Marking |
| 8.2 | Product literature |
| 8.3 | Specifications |
| 9 | Ordering |
| Annex A | (normative) Extruded ceramic tiles with low water absorption $0,5 < E_v \leq 3$ % Group Alb |
| Annex B | (normative) Extruded ceramic tiles $3 < E_v \leq 6$ % Group Alla — Subgroup (Part) 1 |
| Annex C | (normative) Extruded ceramic tiles $3 < E_v \leq 6$ % Group Alla — Subgroup (Part) 2 |
| Annex D | (normative) Extruded ceramic tiles $6 < E_v \leq 10$ % Group Allb — Subgroup (Part) 1 |
| Annex E | (normative) Extruded ceramic tiles $6 < E_v \leq 10$ % Group Allb — Subgroup (Part) 2 |
| Annex F | (normative) Extruded ceramic tiles $E_v > 10$ % Group Alll |
| Annex G | (normative) Dry-pressed ceramic tiles with low water absorption $E_v \leq 0,5$ % Group Bla |
| Annex H | (normative) Dry-pressed ceramic tiles with low water absorption $0,5 < E_v \leq 3$ % Group Blb |
| Annex I | (informative) Intentionally blank |
| Annex J | (normative) Dry-pressed ceramic tiles $3 < E_v \leq 6$ % Group Blla |
| Annex K | (normative) Dry-pressed ceramic tiles $6 < E_v \leq 10$ % Group Bllb |
| Annex L | (normative) Dry-pressed ceramic tiles $E_v > 10$ % Group Blll |
| Annex M | (normative) Extruded ceramic tiles with low water absorption $E_v \leq 0,5$ % Group Ala |

- Annex N (informative) Classification of glazed tiles for floors according to their abrasion resistance**
- Annex O (informative) Intentionally blank**
- Annex P (informative) Test methods**
- Annex Q (informative) Intentionally blank**
- Annex R (informative) Symbols recommended for use**

Page count: 52