

ISO 13319-1:2021 (E)

Determination of particle size distribution — Electrical sensing zone method — Part 1: Aperture/orifice tube method

Contents

	Foreword
1	Scope
2	Normative references
3	Terms and definitions
4	Symbols
5	Principle
6	General operation
6.1	Response
6.2	Size limits
6.3	Effect of coincident particle passage
6.4	Dead time
6.5	Analysis volume
7	Repeatability and reproducibility of counts
7.1	Instrument repeatability
7.2	Method reproducibility/intermediate precision
8	Operational procedures
8.1	General
8.2	Instrument location
8.3	Linearity of the aperture/amplifier system
8.4	Linearity of the counting system
8.5	Choice of electrolyte solution
8.5.1	General
8.5.2	Special considerations for small apertures ($D < 50 \mu\text{m}$)
8.5.3	Special considerations for large apertures ($D > 400 \mu\text{m}$)
8.6	Preparation of electrolyte solution
8.7	Recommended sampling, sample splitting, sample preparation and dispersion
8.7.1	General
8.7.2	Method 1: Using a paste
8.7.3	Method 2: Alternative method applicable to low-density particles of less than $50 \mu\text{m}$
8.7.4	Suspensions and emulsions
8.7.5	Verification of the dispersion
8.8	Choice of aperture(s) and analysis volume(s)
8.9	Clearing an aperture blockage
8.10	Stability of dispersion
8.11	Calibration
8.11.1	General
8.11.2	Calibration procedure — microsphere calibration
9	Analysis
10	Calculation of results
11	Instrument qualification
11.1	General
11.2	Report

Annex A (informative) Derivation of maximum count number to limit coincidence

Annex B (informative) Fishbone diagram for method development

Annex C (informative) Calibration and control of frequently used apertures

Annex D (informative) Mass integration method for calibration and mass balance

- D.1 General
- D.2 Calibration procedure
 - D.2.1 General
 - D.2.2 Volume V_m of analysed suspension
 - D.2.3 Effective density of particles
 - D.2.4 Sample preparation
 - D.2.5 Determination of the calibration factor
 - D.2.6 Secondary calibration
 - D.2.7 Example of calibration by mass integration
- D.3 Mass balance
 - D.3.1 General
 - D.3.2 Sample preparation
 - D.3.3 Procedure
 - D.3.4 Calculations
 - D.3.5 Results
 - D.3.6 Report
 - D.3.7 Theoretical example of mass balance

Annex E (informative) Calibration for the measurement of porous and conductive particles

- E.1 General
- E.2 Particles of conductive materials
- E.3 Porous particles
 - E.3.1 General
 - E.3.2 Sample preparation
 - E.3.3 Microscopy and ESZ measurements
- E.4 Calculations for microscopy
 - E.4.1 General
 - E.4.2 Calculations

Annex F (informative) Technique using two (or more) apertures

- F.1 General
- F.2 Separation
- F.3 Calibration
- F.4 Analysis

Annex G (informative) Chi-squared test of the correctness of instrument operation or sample preparation

- G.1 General
- G.2 Theory
 - G.2.1 General
- G.3 Worked examples

Page count: 34