

DIN 4102-24:2022-12 (E)

Fire behaviour of building materials and building components - Part 24: Assessment of the reaction to fire behaviour of external wall claddings using the base fire test method for façades

Contents

Page

Foreword	4
1 Scope	6
2 Normative references	6
3 Terms and definitions.....	7
4 Test apparatus	10
4.1 Test stand.....	10
4.2 Substrate	10
4.3 Test fire	11
4.4 Test hall	12
4.5 Supply air and extract air conditions.....	12
4.6 Calibration test.....	13
5 Test specimens.....	15
5.1 Dimensions.....	15
5.2 Conditioning.....	15
6 Measurement and registration data	16
6.1 General	16
6.2 Recordings using a video camera and photo camera	17
6.3 Temperature measurements at the test specimen	17
6.3.1 General	17
6.3.2 In front of the test specimen	17
6.3.3 In the test specimen.....	17
6.4 Observations during the test time	17
6.4.1 Fire propagation.....	17
6.4.2 Changes to the test set-up.....	17
6.4.3 Droplets (burning and not burning)	18
6.4.4 Smoke generation	18
6.5 Observations made after the end of the test.....	18
6.6 Glowing combustion and smouldering	18
7 Testing	19
7.1 General	19
7.2 Test time	19
8 Test report.....	19
Annex A (normative) Illustrations of the test stand and the set-up of the wood crib	22
Annex B (normative) Standard instrumentation — Temperature measurement points in front of test specimen.....	26
Annex C (normative) System-specific provisions — ETICS with EPS insulation	28
C.1 Conditioning.....	28
C.2 System-specific instrumentation	28
Annex D (normative) Calibration procedure and calibration data — 200 kg wood crib	32
Bibliography	38

Figures

Figure 1 — Test procedure	16
Figure A.1 — Test stand	22
Figure A.2 — Set-up of wood crib and position on test stand	23
Figure A.3 — Fastening the wood crib.....	23
Figure A.4 — Arrangement of grating (top) and arrangement of wood crib (bottom) on the test stand	24
Figure A.5 — Arrangement of support points with masonry bricks [see a) and b)] and variant for support with rollers [see c)].....	25
Figure A.6 — Standard minimum distances of test stand wings to the enclosing walls and minimum area (shaded) in front of test stand	25
Figure B.1 — Arrangement of temperature measurement points in front of test specimen (view).....	26
Figure B.2 — Arrangement of temperature measurement points in front of test specimen (section).....	27
Figure C.1 — Arrangement of wood crib and the temperature measurement points inside and in front of the test specimen (horizontal section)	29
Figure C.2 — Arrangement of temperature measurement points inside the test specimen (view)	30
Figure C.3 — Arrangement of temperature measurement points E and F in the corner for a test specimen thickness > 350 mm in front of the test specimen and inside the test specimen (horizontal section)	31
Figure D.1 — Example of mass loss of the wood crib.....	32
Figure D.2 — Heat release rate derived from Figure D.1 and calculated heat release rate as permitted in 4.6 between 300 s and 1 500 s (dashed lines)	33
Figure D.3 — Arrangement of temperature measurement points in front of test stand surface (view).....	34
Figure D.4 — Example of an isotherm plot determined at the temperature measurement points as in Figure D.3	35
Figure D.5 — Arrangement of the wood crib and the temperature measurement points for calibration.....	36
Figure D.6 — Set-up of wood crib for calibration (view).....	37