

# DIN EN 680:2006-03 (E)

## Determination of the drying shrinkage of autoclaved aerated concrete

---

<b>Contents</b>		<b>Page</b>
Foreword .....		3
<b>1</b>	<b>Scope .....</b>	<b>4</b>
<b>2</b>	<b>Normative references .....</b>	<b>4</b>
<b>3</b>	<b>Principle .....</b>	<b>4</b>
<b>4</b>	<b>Apparatus .....</b>	<b>4</b>
<b>5</b>	<b>Test specimens .....</b>	<b>5</b>
<b>5.1</b>	<b>Sample .....</b>	<b>5</b>
<b>5.2</b>	<b>Shape and size of the test specimens .....</b>	<b>5</b>
<b>5.3</b>	<b>Number of test specimens .....</b>	<b>5</b>
<b>5.4</b>	<b>Preparation of test specimens .....</b>	<b>6</b>
<b>5.5</b>	<b>Measurement of dimensions of test specimens and determination of their volume .....</b>	<b>6</b>
<b>5.6</b>	<b>Conditioning of test specimens .....</b>	<b>7</b>
<b>6</b>	<b>Testing procedure .....</b>	<b>7</b>
<b>6.1</b>	<b>Drying storage in a climate at <math>(20 \pm 2)</math> °C and <math>(45 \pm 5)</math> % relative humidity and determination of length changes and variations of mass .....</b>	<b>7</b>
<b>6.2</b>	<b>Drying of test specimens at <math>(105 \pm 5)</math> °C .....</b>	<b>7</b>
<b>7</b>	<b>Test results .....</b>	<b>8</b>
<b>7.1</b>	<b>Calculation of relative length change .....</b>	<b>8</b>
<b>7.2</b>	<b>Calculation of moisture content .....</b>	<b>8</b>
<b>7.3</b>	<b>Determination of the conventional reference value of drying shrinkage .....</b>	<b>8</b>
<b>7.4</b>	<b>Determination of the total value of drying shrinkage .....</b>	<b>9</b>
<b>7.5</b>	<b>Calculation of the dry density .....</b>	<b>9</b>
<b>8</b>	<b>Test report .....</b>	<b>9</b>