

# DIN EN 680:2006-03 (E)

## Determination of the drying shrinkage of autoclaved aerated concrete

---

<b>Contents</b>		<b>Page</b>
Foreword .....		3
1	Scope .....	4
2	Normative references .....	4
3	Principle .....	4
4	Apparatus .....	4
5	Test specimens .....	5
5.1	Sample .....	5
5.2	Shape and size of the test specimens .....	5
5.3	Number of test specimens .....	5
5.4	Preparation of test specimens .....	6
5.5	Measurement of dimensions of test specimens and determination of their volume .....	6
5.6	Conditioning of test specimens .....	7
6	Testing procedure .....	7
6.1	Drying storage in a climate at $(20 \pm 2)$ °C and $(45 \pm 5)$ % relative humidity and determination of length changes and variations of mass .....	7
6.2	Drying of test specimens at $(105 \pm 5)$ °C .....	7
7	Test results .....	8
7.1	Calculation of relative length change .....	8
7.2	Calculation of moisture content .....	8
7.3	Determination of the conventional reference value of drying shrinkage .....	8
7.4	Determination of the total value of drying shrinkage .....	9
7.5	Calculation of the dry density .....	9
8	Test report .....	9