

ISO 18675:2022-05 (E)

Dentistry - Machinable ceramic blanks

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
3.1	Materials	1
3.2	Properties	2
3.3	Types of blanks	2
3.4	Test piece	2
4	Homogeneity of partially sintered zirconia blanks	3
4.1	Classification	3
4.2	Determination of the shrinkage factor, d	3
4.2.1	Blanks characterized by one shrinkage factor for all three dimensions in space	3
4.2.2	Blanks characterized by two or three shrinkage factors	5
4.3	Recommendations	6
4.4	Test report	6
5	Warpage	7
5.1	Test method	7
5.1.1	Large zirconia blanks	7
5.1.2	Medium- and small-size zirconia blanks	8
5.2	Recommendations	8
5.3	Test report	9
6	Dimensional stability post machining crystallization of glass ceramics	9
6.1	General	9
6.2	Test method	9
6.2.1	Sample preparation	9
6.2.2	Characterization before heat treatment	10
6.2.3	Heat treatment	11
6.2.4	Characterization after heat treatment	11
6.3	Test report	12
7	Machining damage	13
7.1	General	13
7.2	Test methods	13
7.3	Test report	13
8	Machinability using the merlon fracture test	14
8.1	General	14
8.2	Test method	15
8.2.1	Dimensions of test geometries	15
8.2.2	Machining	16
8.2.3	Characterization of milled specimen	16
8.3	Recommendations	17
8.4	Test report	17
Bibliography		19