

DIN EN 14879-6:2010-04 (E)

Organic coating systems and linings for protection of industrial apparatus and plants against corrosion caused by aggressive media - Part 6: Combined linings with tile and brick layers

Contents		Page
Foreword		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	General	7
4.1	Steel vessels and apparatus	7
4.1.1	Calculating the dimensions of brick-lined steel vessels	7
4.1.2	Dimensional tolerances (for steel and non-ferrous vessels)	9
4.1.3	Construction of steel vessels	9
4.1.4	Installation of brick-lined vessels	10
4.1.5	Leak tests	10
4.1.6	Repairs and modifications	10
4.2	Concrete vessels and apparatus	10
4.2.1	Calculating the dimensions of brick-lined concrete vessels	10
4.2.2	Dimensional tolerances	10
4.2.3	Requirements to the concrete construction	10
4.3	Substrate preparation	10
4.4	Sealing layer	10
4.5	Service layer	11
4.5.1	Bedding and jointing mortar/cement	11
4.5.2	Jointing materials for expansion joints	17
4.5.3	Semi-finished products	17
4.6	Combined lining system	20
4.7	Selection criteria	21
4.7.1	Type and frequency of fluid loading	21
4.7.2	Thermal loading	22
4.7.3	Changes in temperature	22
4.7.4	Mechanical loading	22
4.7.5	Weather factors	23
4.8	Materials manufacturer	23
4.9	Applicator	23
4.10	Application	23
4.10.1	Sealing layers	23
4.10.2	Service layer	24
4.10.3	General requirements	27
4.11	Protected objects	27
5	Requirements	27
5.1	Fluid load, chemical resistance and tightness	27
5.2	Thermal loading	27
5.3	Temperature change loading	28
5.4	Mechanical loading	28
5.5	Anti-slip protection	29
5.6	Crack bridging	29
5.7	Adhesion strength	29

5.8	Ageing behaviour	29
5.9	Weathering behaviour	29
5.10	Concrete compatibility	29
5.11	Behaviour in cleaning and neutralization processes	29
5.12	Capability of dissipating static charges	29
5.13	Behaviour in fire	30
6	Testing	30
6.1	General	30
6.2	Receiving inspection of coating/lining materials	30
6.2.1	Inspection of materials, components and their markings	30
6.2.2	Checking storage conditions	30
6.3	Testing of combined lining systems during application	30
6.3.1	Ambient conditions	30
6.3.2	Sealing layer	31
6.3.3	Service layer	31
6.3.4	Documentation	31
6.4	Suitability testing	31
6.4.1	General	31
6.4.2	Testing of combined linings	32
Annex A (informative) Selection criteria for surface protection systems		36
A.1	Load profiles and suitable surface protection systems for floors and walls	36
A.2	Load profiles and suitable surface protection systems for collecting basins	37
A.3	Load profiles and suitable protection for production plant floors	38
A.4	Load profiles and suitable protection for collecting basins, gutters, channels, pipes, etc	39
A.5	Load profiles and suitable protection for containers	40
Annex B (normative) Overview of verification of suitability for combined linings		41
Annex C (normative) Testing the dissipation capability		42
C.1	General	42
C.1.1	Dissipation resistance	42
C.1.2	Ground dissipating resistance	42
C.2	Testing the dissipation resistance of test samples	42
C.2.1	Instruments	42
C.2.2	Test procedure	42
C.2.3	Test report	42
C.3	Measuring the ground dissipation resistance on the laid surface protection system	43
C.3.1	Instruments	43
C.3.2	Preparation	43
C.3.3	Test procedure	43
C.3.4	Test report	44
Annex D (normative) Test methods for tolerances and limit deviations		45
D.1	Scope and purpose	45
D.2	Tolerances and limit deviations	45
D.2.1	Cylindrical vessel	45
D.2.2	Flat-sided vessels	47
D.3	Test methods	47
D.3.1	General	47
D.3.2	Cylindrical vessel, cylindrical part	47
D.3.3	Shop-fabricated cylindrical vessel, flat base	49
D.3.4	Flat-sided vessels, angular horizontal projection (Determination of the flatness of the faces)	50
Annex E (informative) A-deviations		52
Bibliography		53