

DIN EN 13480-8:2007-06 (E)

Metallic industrial piping - Part 8: Additional requirements for aluminium and aluminium alloy piping

Contents		Page
Foreword		4
1	Scope	5
2	Normative references	5
3	Terms, definitions, symbols and units	6
4	General requirements	6
5	Materials	7
5.1	General	7
5.2	Material grouping system	7
5.3	Elongation after fracture	8
5.4	Chemical composition	8
5.5	Lamellar tearing	8
5.6	Design temperature and properties	8
5.7	Prevention of brittle fracture	9
5.8	Specific requirements for fasteners made of aluminium and aluminium alloys	9
5.9	Lined piping	9
5.10	Clad products	9
5.11	Technical delivery conditions for welding consumables	9
6	Design	9
6.1	General	9
6.2	Time-independent nominal design stress	9
6.3	Straight pipes	10
6.4	Pipe bends and elbows	10
6.5	Mitre bends	10
6.6	Socket welds	12
6.7	Designing with transition joints	13
7	Fabrication and installation	13
7.1	General	13
7.2	Material grouping	13
7.3	Tolerances	13
7.4	Cutting and bevelling	14
7.5	Bending and other forming	14
7.6	Welding	17
8	Inspection and testing	19
8.1	General	19
8.2	Formed pressure retaining parts	19
8.3	Welding	21
8.4	Visual and non-destructive testing of welds	21
8.5	VT and NDT Methods	22
8.6	Production test plates for welded pipes	23
9	Final assessment and documentation	24
9.1	General	24
9.2	Pneumatic pressure test	24

9.3	Documentation for components	25
	Annex A (informative) Dimensional tolerances	27
	Annex B (normative) Transition joints	29
B.1	General	29
B.2	Materials	29
B.3	Design	29
B.4	Permanent joining process	29
Issue 1 (2007-03)	B.5 Testing	30
B.6	Marking	30
B.7	Documentation	31
B.8	Protection against overheating	31
	Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC	33
	Bibliography	35
	Figures Figure 6.5-1 -- Mitre bend	12
	Figure 7.6.3-1 -- Socket welds	18
	Figure A.1 -- Dimensional details of spools	28
	Tables Table 5.2-1 -- Grouping system based on CEN ISO/TR 15608:2005 and allowable materials of construction based on EN 12392:2000 using the EN AW numbers according to EN 573-3	7
	Table 6.2-1 -- Design stresses for aluminium and aluminium alloy material	10
	Table 6.2-2 -- Allowable design strength values for 6 000 series aluminium alloys in the welded condition (see 5.6)	10
	Table 6.5.1 -- Special symbols for subclause 6.5	12
	Table 7.3-1 -- Tolerances for welded pipes	14
	Table 7.5-3 Heat treatment after hot forming	16
	Table 8.2-1 -- Destructive testing of formed and heat treated parts	20
	Table 8.4-1 -- Extent of testing for circumferential, branch, socket and seal welds	21
	Table 8.4-2 -- Extent of VT and NDT for longitudinal welds and spiral welded tubes / pipes	22
	Table 8.5-1 -- Techniques, methods, acceptance criteria	23
	Table 8.6-1 -- Production test plates for welded pipes according to 8.6 a)	24
	Table 8.6-2 -- Required tests and acceptance criteria for production test plates	24
	Table 9.2-1 -- Extent of NDT in case of pneumatic pressure test according to 9.2b)	25
	Table A.1 -- Tolerances	27
	Table ZA.1 -- Correspondence between this European Standard and Directive 97/23/EC	33