

ISO 636:2024-09 (E)

Welding consumables - Rods, wires and deposits for tungsten inert gas welding of non-alloy and fine-grain steels - Classification

Contents		Page
Foreword		iv
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Classification	2
4.1	General	2
4.2	Classification systems	2
5	Symbols and requirements	2
5.1	Symbol for the product/process	2
5.2	Symbol for strength and elongation of all-weld metal	2
5.3	Symbol for impact properties of all-weld metal	3
5.3.1	System A - Classification by yield strength and 47 J impact energy	3
5.3.2	System B - Classification by tensile strength and 27 J impact energy	3
5.4	Symbol for the chemical composition of rods or wires	4
6	Mechanical tests	8
6.1	Mechanical tests and conditions	8
6.2	Preheating and interpass temperatures	8
6.3	Welding conditions and pass sequence	9
6.4	PWHT condition	9
7	Chemical analysis	9
8	Rounding procedure	9
9	Retesting	10
10	Technical delivery conditions	10
11	Designation examples	10
11.1	General	10
11.2	Example 1 - Classification by yield strength and 47 J impact energy - System A	10
11.3	Example 2 - Classification by tensile strength and 27 J impact energy - System B	10
11.4	Example 3 - Classification by yield strength and 47 J impact energy - System A	11
11.5	Example 4 - Classification by tensile strength and 27 J impact energy - System B	11
11.6	Example 4 - Classification by tensile strength and 27 J impact energy - System B	12
Bibliography		13