

# ISO 17641-2 :2005-03 (E)

Destructive tests on welds in metallic materials\_ - Hot cracking tests for weldments\_ - Arc welding processes\_ - Part\_2: Self-restraint tests

---

## Contents

page

Foreword.....	v
<b>1</b> <b>Scope</b> .....	<b>1</b>
<b>2</b> <b>Normative references</b> .....	<b>1</b>
<b>3</b> <b>Terms and definitions</b> .....	<b>1</b>
<b>4</b> <b>Symbols, designations and units</b> .....	<b>1</b>
<b>5</b> <b>Principle</b> .....	<b>2</b>
<b>6</b> <b>Description of the tests</b> .....	<b>3</b>
<b>6.1</b> <b>T-joint weld cracking tests</b> .....	<b>3</b>
<b>6.1.1</b> <b>General</b> .....	<b>3</b>
<b>6.1.2</b> <b>Dimension of the test pieces</b> .....	<b>3</b>
<b>6.1.3</b> <b>Preparation of the test pieces</b> .....	<b>5</b>
<b>6.1.4</b> <b>Welding of the test pieces</b> .....	<b>6</b>
<b>6.1.5</b> <b>Examination of the test piece</b> .....	<b>6</b>
<b>6.1.6</b> <b>Test report</b> .....	<b>6</b>
<b>6.2</b> <b>Weld metal tensile test</b> .....	<b>6</b>
<b>6.2.1</b> <b>General</b> .....	<b>6</b>
<b>6.2.2</b> <b>Test specimen</b> .....	<b>6</b>
<b>6.2.3</b> <b>Examination of the test specimen</b> .....	<b>7</b>
<b>6.2.4</b> <b>Test report</b> .....	<b>8</b>
<b>6.3</b> <b>Longitudinal bend test</b> .....	<b>8</b>
<b>6.3.1</b> <b>General</b> .....	<b>8</b>
<b>6.3.2</b> <b>Test weld</b> .....	<b>8</b>
<b>6.3.3</b> <b>Test specimen</b> .....	<b>8</b>
<b>6.3.4</b> <b>Surface preparation</b> .....	<b>10</b>
<b>6.3.5</b> <b>Testing</b> .....	<b>10</b>
<b>6.3.6</b> <b>Examination of the test specimen</b> .....	<b>10</b>
<b>6.3.7</b> <b>Test report</b> .....	<b>10</b>
<b>Annex A</b> (informative) <b>Test report for T-joint weld cracking test</b> .....	<b>11</b>
<b>Annex B</b> (informative) <b>Test report for weld metal tensile test</b> .....	<b>12</b>
<b>Annex C</b> (informative) <b>Test report for longitudinal bend test</b> .....	<b>13</b>
<b>Annex ZA</b> (normative) <b>List of corresponding European and International Standards for which equivalents are not given in the text</b> .....	<b>14</b>