

DIN 2559-2:2007-09 (E)

Preparation of joints for welding - Part 2: Matching of inside diameters for circumferential welds on seamless tubes

Contents		Page
Foreword		3
1 Scope		4
2 Normative references		4
3 Symbols and definitions		4
4 Dimensions		5
4.1 General		5
4.2 Tolerances		6
4.3 Calculating the matching diameter		6
5 Joint preparation		9
Figures Figure 1 -- Joint preparation as in DIN EN ISO 9692-1, Ref. no. 1.3, matched		5
Figure 2 -- Joint preparation as in DIN EN ISO 9692-1, Ref. no. 1.6, matched		5
Figure 3 -- Relationship between equations in Table 2 and outside diameters and wall thicknesses in Table 6		7
Tables Table 1 -- Tolerances for d_p		6
Table 2 -- Equations for calculating d_p for tubes with outside diameter as in DIN EN 10216-1:2004-07, Table 6, or DIN EN 10216-2:2004-07, Table 7		6
Table 3 -- Equations for calculating d_p for tubes with inside diameter and wall thickness as in DIN EN 10216-2:2004-07, Table 8, or inside diameter and minimum wall thickness as in DIN EN 10216-2:2004-07, Table 10		7
Table 4 -- Equations for calculating d_p for tubes with outside diameter and minimum wall thickness as in DIN EN 10216-2:2004-07, Table 9		8
Tabelle 5 -- Equations for calculating d_p for tubes ordered cold-finished with outside diameter and wall thickness as in DIN EN 10216-2:2004-07, Table 11		8
Table 6 -- Matching diameter d_p as in Table 2 for tubes with outside diameter as in DIN EN 10216-1:2004-07, Table 6, or DIN EN 10216-2:2004-07, Table 7		10
Table 7 -- Matching diameter d_p as in Table 3 for tubes with outside diameter as in DIN EN 10216-2:2004-07, Table 9		13
Table 8 -- Matching diameter d_p as in Table 6 for cold-finished tubes with outside diameter as in DIN EN 10216-2:2004-07, Table 11		16
Table 9 -- Minimum allowable wall thickness t_p for tubes with outside diameter as in DIN EN 10216-1:2004-07, Table 6, or as in DIN EN 10216-2:2004-07, Table 7		19
Table 10 -- Minimum allowable wall thickness t_p for cold-finished tubes with outside diameter as in DIN EN 10216-2:2004-07, Table 11		20