

DIN EN ISO/IEC 80079-20-1:2020-09 (E)

Explosive atmospheres - Part 20-1: Material characteristics for gas and vapour classification - Test methods and data (ISO/IEC 80079-20-1:2017, including Cor 1:2018)

CONTENTS

EUROPEAN FOREWORD	5
ANNEX ZA (informative) Relationship between this European Standard and the essential requirements of Directive 2014/34/EU aimed to be covered	6
FOREWORD	7
1 Scope	9
2 Normative references	9
3 Terms and definitions	9
4 Classification of gases and vapours	11
4.1 General	11
4.2 Classification according to the maximum experimental safe gap (MESG)	11
4.3 Classification according to the minimum igniting current ratio (MIC ratio)	12
4.4 Classification according to the similarity of chemical structure	12
4.5 Classification of mixtures of gases	12
5 Data for flammable gases and vapours, relating to the use of equipment	13
5.1 Determination of the properties	13
5.1.1 General	13
5.1.2 Equipment group	13
5.1.3 Flammable limits	13
5.1.4 Flash point (FP)	13
5.1.5 Temperature class	14
5.1.6 Minimum igniting current (MIC)	14
5.1.7 Auto-ignition temperature (AIT)	14
5.2 Properties of particular gases and vapours	14
5.2.1 Coke oven gas	14
5.2.2 Ethyl nitrite	14
5.2.3 MESG of carbon monoxide	14
5.2.4 Methane, Equipment Group IIA	15
6 Method of test for the maximum experimental safe gap (MESG)	15
6.1 Outline of method	15
6.2 Test apparatus	15
6.2.1 General	15
6.2.2 Material and mechanical strength	16
6.2.3 Exterior chamber	16
6.2.4 Interior chamber	16
6.2.5 Gap adjustment	16
6.2.6 Injection of mixture	16
6.2.7 Position of ignition source	16
6.3 Procedure	16
6.3.1 Preparation of gas mixtures	16
6.3.2 Temperature and pressure	16
6.3.3 Gap adjustment	17

6.3.4	Ignition	17
6.3.5	Observation of the ignition process	17
6.4	Determination of maximum experimental safe gap (MESG)	17
6.4.1	General	17
6.4.2	Preliminary tests	17
6.4.3	Confirmatory tests	17
6.4.4	Reproducibility of maximum experimental safe gaps (MESG).....	17
6.4.5	Tabulated values	18
6.5	Verification of the MESG determination method	18
7	Method of test for auto-ignition temperature (AIT).....	18
7.1	Outline of method	18
7.2	Apparatus	18
7.2.1	General	18
7.2.2	Test vessel and support.....	19
7.2.3	Thermocouples	19
7.2.4	Oven	19
7.2.5	Metering devices	20
7.2.6	Mirror	20
7.2.7	Timer.....	20
7.2.8	Equipment for purging the test vessel with air.....	20
7.2.9	Automated apparatus.....	20
7.3	Sampling, preparation and preservation of test samples	21
7.3.1	Sampling	21
7.3.2	Preparation and preservation.....	21
7.4	Procedure	21
7.4.1	General	21
7.4.2	Sample injection	22
7.4.3	Determination of the auto-ignition temperature (AIT).....	22
7.5	Auto-ignition temperature (AIT)	23
7.6	Validity of results	23
7.6.1	Repeatability	23
7.6.2	Reproducibility.....	23
7.7	Data.....	24
7.8	Verification of the auto-ignition temperature determination method	24
Annex A (normative)	Ovens of test apparatus for the tests of auto-ignition temperature	25
A.1	General.....	25
A.2	“IEC oven”	25
A.3	“DIN oven”	25
Annex B (informative)	Tabulated values	32
Annex C (informative)	Determination of cool flames	86
Annex D (informative)	Volume dependence of auto-ignition temperature.....	88
Bibliography	89
Figure 1	– Test apparatus	15
Figure A.1	– Test apparatus: assembly	26
Figure A.2	– Section A-A (flask omitted)	27
Figure A.3	– Base heater (board made of refractory material)	27

Figure A.4 – Flask guide ring (board made of refractory material)	28
Figure A.5 – Neck heater (board made of refractory material)	28
Figure A.6 – Oven.....	29
Figure A.7 – Lid of steel cylinder.....	30
Figure A.8 – Lid of steel cylinder.....	31
Figure A.9 – Injection of gaseous sample.....	31
Figure C.1 – Additional thermocouple to detect cool flames	86
Figure C.2 – ‘Negative temperature coefficient’ shown for butyl butyrate as an example	87
Figure D.1 – Volume dependence of auto-ignition temperature	88
Table 1 – Classification of temperature class and range of auto-ignition temperatures.....	14
Table 2 – Values for verification of the apparatus	18
Table 3 – Values for verification of the apparatus	24
Table B.1 – Material data.....	34