

ISO/IEC 80079-20-1:2017-12 (E/F)

Explosive atmospheres - Part 20-1: Material characteristics for gas and vapour classification - Test methods and data

Atmosphère s explosives - Partie 20-1: Caractéristiques des produits pour le classement des gaz et des vapeurs - Méthodes et données d'essai

Contents	Page
FOREWORD.....	5
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Classification of gases and vapours.....	9
4.1 General.....	9
4.2 Classification according to the maximum experimental safe gap (MESG).....	9
4.3 Classification according to the minimum igniting current ratio (MIC ratio).....	10
4.4 Classification according to the similarity of chemical structure	10
4.5 Classification of mixtures of gases	10
5 Data for flammable gases and vapours, relating to the use of equipment.....	11
5.1 Determination of the properties	11
5.1.1 General	11
5.1.2 Equipment group	11
5.1.3 Flammable limits.....	11
5.1.4 Flash point (FP).....	11
5.1.5 Temperature class	12
5.1.6 Minimum igniting current (MIC).....	12
5.1.7 Auto-ignition temperature (AIT).....	12
5.2 Properties of particular gases and vapours	12
5.2.1 Coke oven gas.....	12
5.2.2 Ethyl nitrite	12
5.2.3 MESG of carbon monoxide	12
5.2.4 Methane, Equipment Group IIA.....	13
6 Method of test for the maximum experimental safe gap (MESG).....	13
6.1 Outline of method	13
6.2 Test apparatus.....	13
6.2.1 General	13
6.2.2 Material and mechanical strength	14
6.2.3 Exterior chamber	14
6.2.4 Interior chamber	14
6.2.5 Gap adjustment	14
6.2.6 Injection of mixture	14
6.2.7 Position of ignition source.....	14
6.3 Procedure	14
6.3.1 Preparation of gas mixtures	14
6.3.2 Temperature and pressure.....	14
6.3.3 Gap adjustment	15
6.3.4 Ignition	15
6.3.5 Observation of the ignition process.....	15
6.4 Determination of maximum experimental safe gap (MESG).....	15

6.4.1	General	15
6.4.2	Preliminary tests.....	15
6.4.3	Confirmatory tests	15
6.4.4	Reproducibility of maximum experimental safe gaps (MESG).....	15
6.4.5	Tabulated values	16
6.5	Verification of the MESG determination method	16
7	Method of test for auto-ignition temperature (AIT).....	16
7.1	Outline of method	16
7.2	Apparatus	16
7.2.1	General	16
7.2.2	Test vessel and support.....	17
7.2.3	Thermocouples	17
7.2.4	Oven	17
7.2.5	Metering devices	18
7.2.6	Mirror	18
7.2.7	Timer.....	18
7.2.8	Equipment for purging the test vessel with air.....	18
7.2.9	Automated apparatus.....	18
7.3	Sampling, preparation and preservation of test samples	19
7.3.1	Sampling	19
7.3.2	Preparation and preservation.....	19
7.4	Procedure	19
7.4.1	General	19
7.4.2	Sample injection	20
7.4.3	Determination of the auto-ignition temperature (AIT).....	20
7.5	Auto-ignition temperature (AIT).....	21
7.6	Validity of results	21
7.6.1	Repeatability	21
7.6.2	Reproducibility.....	21
7.7	Data.....	22
7.8	Verification of the auto-ignition temperature determination method	22
Annex A (normative)	Ovens of test apparatus for the tests of auto-ignition temperature	23
A.1	General.....	23
A.2	“IEC oven”	23
A.3	“DIN oven”	23
Annex B (informative)	Tabulated values	30
Annex C (informative)	Determination of cool flames	84
Annex D (informative)	Volume dependence of auto-ignition temperature.....	86
Bibliography.....		87
Figure 1 – Test apparatus		13
Figure A.1 – Test apparatus: assembly		24
Figure A.2 – Section A-A (flask omitted)		25
Figure A.3 – Base heater (board made of refractory material)		25
Figure A.4 – Flask guide ring (board made of refractory material)		26
Figure A.5 – Neck heater (board made of refractory material)		26
Figure A.6 – Oven.....		27
Figure A.7 – Lid of steel cylinder.....		28
Figure A.8 – Lid of steel cylinder.....		29
Figure A.9 – Injection of gaseous sample.....		29
Figure C.1 – Additional thermocouple to detect cool flames		84

Figure C.2 – ‘Negative temperature coefficient’ shown for butyl butyrate as an example	85
Figure D.1 – Volume dependence of auto-ignition temperature	86
Table 1 – Classification of temperature class and range of auto-ignition temperatures.....	12
Table 2 – Values for verification of the apparatus	16
Table 3 – Values for verification of the apparatus	22
Table B.1 – Material data.....	32