

DIN EN 295-5:2013-05 (E)

Vitrified clay pipe systems for drains and sewers - Part 5: Requirements for perforated pipes and fittings

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Requirements for pipes and fittings	4
4.1	Material, manufacture, water absorption and appearance	4
4.2	Internal diameter	4
4.3	Length	5
4.4	Deviation from straightness	5
4.5	Angle of curvature and radius of bends	5
4.6	Branch angle of junctions	6
4.7	Perforations	6
4.7.1	General	6
4.7.2	Arrangement of perforations	6
4.7.3	Area of perforations	6
4.8	Crushing strength (FN)	6
4.9	Chemical resistance	7
4.10	Fatigue strength under cyclic load	8
5	Joint assemblies	8
6	Common requirements for pipes and fittings	8
6.1	Reaction to fire	8
6.2	Durability	8
6.3	Dangerous substances	8
7	Designation	9
8	Marking	9
9	Evaluation of conformity	10
9.1	General	10
9.2	Initial type testing	10
9.3	Factory production control (FPC)	10
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of the EU Construction Products Directive		11
ZA.1 Scope and relevant characteristics		11
ZA.2 Procedures for the attestation of conformity of perforated vitrified clay pipes and fittings		12
ZA.2.1 Systems of attestation of conformity		12
ZA.2.2 EC declaration of conformity		13
ZA.3 CE marking		14

ZA.3.1 General	14
ZA.3.2 CE marking on the product	14
ZA.3.3 CE marking in the accompanying documents	15
Bibliography	17