

ISO 11119-3:2020 (E)

Gas cylinders — Design, construction and testing of refillable composite gas cylinders and tubes — Part 3: Fully wrapped fibre reinforced composite gas cylinders and tubes up to 450 l with non-load-sharing metallic or non-metallic liners or without liners

Contents

	Foreword
	Introduction
1	Scope
2	Normative references
3	Terms and definitions
4	Symbols
5	Inspection and testing
6	Materials
6.1	Liner materials
6.2	Composite materials
7	Design and manufacture
7.1	General
7.2	Design submission
7.3	Manufacturing
8	Type approval procedure
8.1	General requirements
8.2	Prototype tests
8.3	New design
8.4	Design variants
8.5	Type approval test procedures and criteria
8.5.1	Proof pressure test
8.5.1.1	Procedure
8.5.1.2	Criteria
8.5.2	Hydraulic elastic expansion test
8.5.2.1	Procedure
8.5.2.2	Criteria
8.5.3	Cylinder burst test
8.5.3.1	Procedure
8.5.3.2	Criteria
8.5.4	Ambient cycle test
8.5.4.1	For cylinders with test pressure equal to, or greater than, 60 bar
8.5.4.1.1	General
8.5.4.1.2	Procedure
8.5.4.1.3	Criteria
8.5.4.2	For cylinders with test pressure less than 60 bar
8.5.4.2.1	Procedure
8.5.4.2.2	Criteria
8.5.5	Vacuum test
8.5.5.1	General
8.5.5.2	Procedure
8.5.5.3	Criteria

- 8.5.6 Environmental cycle test
 - 8.5.6.1 General
 - 8.5.6.2 Procedure
 - 8.5.6.3 Criteria
- 8.5.7 Environmentally assisted stress rupture test
 - 8.5.7.1 Procedure
 - 8.5.7.2 Criteria
- 8.5.8 Flaw test
 - 8.5.8.1 Procedure
 - 8.5.8.2 Criteria
- 8.5.9 Drop/impact test
 - 8.5.9.1 General
 - 8.5.9.2 For cylinders up to and including 50 l water capacity with unspecified gas service and cylinders with liquefied gas service
 - 8.5.9.2.1 Procedure
 - 8.5.9.2.2 Criteria
 - 8.5.9.3 For cylinders over 50 l water capacity
 - 8.5.9.3.1 Procedure
 - 8.5.9.3.2 Criteria
 - 8.5.9.4 For cylinders up to and including 50 l water capacity with dedicated compressed gas service
 - 8.5.9.4.1 Procedure
 - 8.5.9.4.2 Criteria
 - 8.5.9.5 Impact test for tubes over 150 l water capacity
 - 8.5.9.5.1 Procedure
 - 8.5.9.5.2 Criteria
- 8.5.10 High velocity impact (gunfire) test
 - 8.5.10.1 Procedure
 - 8.5.10.2 Criteria
- 8.5.11 Fire resistance test
 - 8.5.11.1 General
 - 8.5.11.2 Procedure
 - 8.5.11.2.1 General
 - 8.5.11.2.2 Horizontal test
 - 8.5.11.2.3 Vertical test
 - 8.5.11.3 Criteria
- 8.5.12 Permeability test
 - 8.5.12.1 General
 - 8.5.12.2 Procedure
 - 8.5.12.3 Criteria
- 8.5.13 Torque test on cylinder neck boss
 - 8.5.13.1 Procedure
 - 8.5.13.2 Criteria
- 8.5.14 Salt water immersion test
 - 8.5.14.1 General
 - 8.5.14.2 Procedure
 - 8.5.14.3 Criteria
- 8.5.15 Leak test
 - 8.5.15.1 Procedure
 - 8.5.15.2 Criteria
- 8.5.16 Pneumatic cycle test
 - 8.5.16.1 General
 - 8.5.16.2 Procedure
 - 8.5.16.3 Criteria
- 8.5.17 Liner burst test
 - 8.5.17.1 General
 - 8.5.17.2 Procedure
 - 8.5.17.3 Criteria
- 8.5.18 Resin shear strength
- 8.5.19 Glass transition temperature
- 8.6 Failure of type approval tests

9 Batch inspection and testing

- 9.1 Liner

- 9.2 Failure of liner batch tests
- 9.3 Overwrap materials
- 9.4 Composite cylinder
- 9.5 Cylinder failure during type approval or batch testing
- 10 Cylinder marking
 - 10.1 General
 - 10.2 Additional marking
- Annex A (informative) Examples of design approval certificate
- Annex B (informative) Specimen test reports
- Annex C (informative) Test report for equivalency
- Annex D (informative) Standardized test requirements for thermally activated pressure relief devices
 - D.1 General
 - D.2 Cylinder test
 - D.2.1 Cylinder set-up
 - D.2.2 Fire source
 - D.2.3 Temperature and pressure measurements
 - D.2.4 General test requirements
 - D.2.5 Test options
 - D.2.5.1 Option A — Controlled release of pressure
 - D.2.5.2 Option B — Fire test until rupture
 - D.3 PRD test
 - D.4 Vent test
 - D.5 System assessment
 - D.5.1 Qualification limit envelope
 - D.5.2 Service limit envelope
 - D.5.3 Acceptable results

Page count: 48