

# ISO 3994:2007-08 (E)

## Plastics hoses - Helical-thermoplastic-reinforced thermoplastics hoses for suction and discharge of aqueous materials - Specification

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
Introduction .....		v
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>2</b>
<b>4</b>	<b>Classification .....</b>	<b>2</b>
<b>5</b>	<b>Materials and construction .....</b>	<b>2</b>
<b>6</b>	<b>Dimensions and tolerances .....</b>	<b>2</b>
<b>6.1</b>	<b>Nominal bores, internal diameters and tolerances .....</b>	<b>2</b>
<b>6.2</b>	<b>Length tolerances .....</b>	<b>2</b>
<b>7</b>	<b>Performance requirements .....</b>	<b>3</b>
<b>7.1</b>	<b>Hydrostatic testing at 23 °C ± 2 °C .....</b>	<b>3</b>
<b>7.2</b>	<b>Hydrostatic testing at 55 °C ± 2 °C .....</b>	<b>4</b>
<b>7.3</b>	<b>Maximum working pressure .....</b>	<b>4</b>
<b>7.4</b>	<b>Tensile adhesion test .....</b>	<b>5</b>
<b>7.5</b>	<b>Vacuum test .....</b>	<b>5</b>
<b>7.6</b>	<b>Reinforcement fracture test .....</b>	<b>5</b>
<b>7.7</b>	<b>Minimum bend radius .....</b>	<b>6</b>
<b>7.8</b>	<b>Cold-bend radius .....</b>	<b>6</b>
<b>7.9</b>	<b>Loss in mass on heating .....</b>	<b>6</b>
<b>7.10</b>	<b>Exposure to xenon-arc lamp .....</b>	<b>6</b>
<b>8</b>	<b>Type, routine and production testing .....</b>	<b>7</b>
<b>9</b>	<b>Marking .....</b>	<b>7</b>
<b>10</b>	<b>Recommendations for packing and storage .....</b>	<b>7</b>
<b>Annex A (normative) Tensile adhesion test .....</b>		<b>8</b>
<b>Annex B (normative) Vacuum test .....</b>		<b>10</b>
<b>Annex C (normative) Reinforcement fracture test .....</b>		<b>11</b>
<b>Annex D (normative) Type and routine tests .....</b>		<b>13</b>
<b>Annex E (informative) Recommended tests for production testing .....</b>		<b>14</b>