

DIN EN 1910:2016-08 (E)

Wood flooring and wood panelling and cladding - Determination of dimensional stability

Contents		Page
European foreword		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Principle	5
5	Test equipment	5
5.1	Conditioning room or enclosure	5
5.2	Stabilizing room or enclosure	6
5.3	Trays	6
5.4	Measuring equipment	6
5.5	Scales	6
5.6	Oven	6
6	Test specimens	6
6.1	Dimensions and shape	6
6.2	Sampling	7
6.3	Conditioning	7
7	Measurements	7
7.1	Mass	7
7.2	Dimensions of the test specimen	7
7.3	Warp	7
7.3.1	General	7
7.3.2	Twist	7
7.3.3	Procedure	7
7.3.4	Expression of results	9
7.4	Moisture content	9
8	Procedure	9
8.1	Initial measurements	9
8.2	Exposure to the humid climate	9
8.3	Measurements after stabilization in the humid climate	9
8.4	Exposure to the dry climate	9
8.5	Measurements after stabilization in the dry climate	10
8.6	Oven drying	10
9	Calculation and expression of the results of a test specimen	10
9.1	Moisture content	10
9.2	Dimensional changes	10
9.3	Warp	10
9.3.1	Cup	10
9.3.2	Spring	11
9.3.3	Bow	11
9.3.4	Twist	11
10	Accuracy of the 10 test specimens	11

10.1	Dimensional changes	11
10.2	Warp	11
11	Test report	11
	Bibliography	13