

DIN EN 113-2:2021-02 (E)

Durability of wood and wood-based products - Test method against wood destroying basidiomycetes - Part 2: Assessment of inherent or enhanced durability

Contents		Page
European foreword		4
Introduction		5
1	Scope	6
2	Normative references	6
3	Terms and definitions	6
4	Principle	6
5	Test material and apparatus	7
5.1	Biological material	7
5.1.1	Test fungi	7
5.1.2	Wood as virulence control	8
5.2	Products and reagents	9
5.3	Apparatus	9
5.3.1	Culture vessels	9
5.3.2	Drying oven	9
5.3.3	Desiccators	9
5.3.4	Conditioning chamber	9
5.3.5	Culture chamber	9
5.3.6	Test specimens supports	9
5.3.7	Equipment for steam sterilization or access to a radiation source	10
5.3.8	Ordinary laboratory equipment	10
6	Test specimens	10
6.1	Species and source of wood	10
6.2	Wood quality	10
6.3	Provision of the test specimens	10
6.4	Dimensions of test specimens	11
6.5	Number and distribution of test specimens	11
7	Procedure	12
7.1	Preparation of the wood test specimens	12
7.1.1	Virulence control	12
7.1.2	Wood under test	12
7.2	Exposure to fungi	13
7.3	Culture conditions and duration of test	13
7.4	Assessment of test	13
7.4.1	Examination of the test specimens	13
7.4.2	Validity of results	14
7.4.3	Assessment of results	14
8	Statement of results	14
9	Test report	15
Annex A(informative) Guidance on sampling		16

Annex B(normative) Methods of sterilization	18
Annex C(informative) Culture vessels	19
Annex D(informative) Example of a test report	22
Annex E(informative) Test fungi	23
Annex F(informative) Assessment of results	27
Bibliography	29