

# ISO 5999:2007-11 (E)

## Flexible cellular polymeric materials - Polyurethane foam for load-bearing applications excluding carpet underlay - Specification

---

| <b>Contents</b>   |  | <b>Page</b> |
|---|--|-------------|
| Foreword .....  |  | iv          |
| <b>1</b>  | <b>Scope .....</b>                                     | <b>1</b>    |
| <b>2</b>  | <b>Normative references .....</b>                      | <b>1</b>    |
| <b>3</b>  | <b>Classification .....</b>                            | <b>2</b>    |
| <b>3.1</b>  | <b>Type .....</b>                                      | <b>2</b>    |
| <b>3.2</b>  | <b>Class .....</b>                                     | <b>2</b>    |
| <b>3.3</b>  | <b>Grade .....</b>                                     | <b>6</b>    |
| <b>4</b>  | <b>Material .....</b>                                  | <b>7</b>    |
| <b>5</b>  | <b>Construction .....</b>                              | <b>7</b>    |
| <b>6</b>  | <b>Surface condition .....</b>                         | <b>7</b>    |
| <b>7</b>  | <b>Odour .....</b>                                     | <b>7</b>    |
| <b>8</b>  | <b>Colour .....</b>                                    | <b>7</b>    |
| <b>9</b>  | <b>Component mass and density .....</b>                | <b>7</b>    |
| <b>10</b>   | <b>Dimensions .....</b>                                | <b>8</b>    |
| <b>11</b>   | <b>Physical and chemical requirements .....</b>        | <b>8</b>    |
| <b>12</b>   | <b>Burning characteristics .....</b>                   | <b>10</b>   |
| <b>13</b>   | <b>Test methods .....</b>                              | <b>10</b>   |
| <b>13.1</b>   | <b>Test conditions .....</b>                           | <b>10</b>   |
| <b>13.2</b>   | <b>Density .....</b>                                   | <b>10</b>   |
| <b>13.3</b>   | <b>Hardness .....</b>                                  | <b>10</b>   |
| <b>13.4</b>   | <b>Resilience .....</b>                                | <b>10</b>   |
| <b>13.5</b>   | <b>Compression set .....</b>                           | <b>11</b>   |
| <b>13.6</b>   | <b>Dynamic fatigue by constant-load pounding .....</b> | <b>11</b>   |
| <b>13.7</b>   | <b>Tensile strength and elongation at break .....</b>  | <b>11</b>   |
| <b>13.8</b>   | <b>Burning behaviour .....</b>                         | <b>11</b>   |
| <b>13.9</b>   | <b>Heat ageing .....</b>                               | <b>11</b>   |
| <b>13.10</b>  | <b>Humidity ageing .....</b>                           | <b>11</b>   |
| <b>14</b>   | <b>Marking .....</b>                                   | <b>11</b>   |
| <b>Annex A (informative) Typical applications for each class of material .....</b>  |  | <b>12</b>   |
| <b>Annex B (informative) Burning properties of flexible polyurethane foam and recommendations regarding its use .....</b> |  | <b>13</b>   |
| <b>Annex C (informative) Main details of revision .....</b>   |  | <b>15</b>   |