

DIN EN ISO 21079-2:2008-08 (E)

Chemical analysis of refractories containing alumina, zirconia and silica -
Refractories containing 5 % to 45 % of ZrO₂ (alternative to the X-ray
fluorescence method) - Part 2: Wet chemical analysis (ISO 21079-2:2008)

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Determination of silicon(IV) oxide.....	5
4	Determination of aluminium oxide.....	7
5	Determination of iron(III) oxide.....	10
6	Determination of titanium(IV) oxide	11
7	Determination of calcium oxide	14
8	Determination of magnesium oxide.....	15
9	Determination of sodium oxide by flame photometry	16
10	Determination of potassium oxide by flame photometry	17
11	Determination of chromium(III) oxide using diphenylcarbazide.....	18
12	Determination of zirconium oxide (including hafnium oxide) by mandelic acid (α -hydroxybenzeneacetic acid) gravimetric method.....	19
13	Calculation and expression of test results	20
14	Test report	20
Bibliography		21