

DIN EN 843-6:2009-12 (E)

Advanced technical ceramics - Mechanical properties of monolithic ceramics at room temperature - Part 6: Guidance for fractographic investigation

Contents		Page
Foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
3.1	General terms	4
3.2	Terms classifying inherently volume-distributed fracture origins	4
3.3	Terms classifying inherently surface-distributed fracture origins	5
3.4	Terms classifying features on fracture surfaces	6
4	Significance and use	6
5	Apparatus	6
5.1	Preparation and cleaning facilities	6
5.2	Observational facilities	7
6	Recommended procedure	9
6.1	Outline	9
6.2	Specimen storage and cleaning of fracture surfaces	9
6.3	Visual inspection	9
6.4	Optical microscope examination	10
6.5	Identification of major fracture surface features	10
6.6	Scanning electron microscope examination	12
6.7	Identification of fracture origin	12
6.8	Identification of chemical inhomogeneity at fracture origin	13
6.9	Drawing conclusions	13
7	Report	13
Annex A (informative) Crack patterns in ceramic bodies		14
Annex B (informative) Examples of general features of fracture surfaces		17
Annex C (informative) Examples of procedure for fracture origin identification		19
C.1	Single large pores	20
C.2	Agglomerates	22
C.3	Large grains	24
C.4	Compositional inhomogeneities	26
C.5	Delaminations	28
C.6	Handling damage	30
C.7	Machining damage	31
C.8	Oxidation pitting	33
C.9	Complex origins	35
C.10	No obvious origins	36
Annex D (informative) Use of fracture mechanical information to aid fractography		37
D.1	Fracture stress and origin size	37

D.2	Fracture stress and fracture mirror size	40
Annex E (informative)	Example layout of reporting pro-forma	42
Bibliography		44